# Enhanced Initial Cell Responses to Chemically Modified Anodized Titanium

Ryo Jimbo, DDS;\* Takashi Sawase, DDS, PhD;\* Koumei Baba, MS, PhD;<sup>†</sup> Tadafumi Kurogi, DDS, PhD;<sup>‡</sup> Yasuaki Shibata, DDS, PhD;<sup>§</sup> Mitsuru Atsuta, DDS, PhD\*

## ABSTRACT

*Background:* Previously, we reported that anodized porous titanium implants have photocatalytic hydrophilicity. However, this effect was not always sufficient for the significant improvement of bone apposition.

*Purpose*: The purpose of this study was to improve the photocatalytic properties of porous titanium implants by the fluoride modification of the anodized titanium dioxide  $(TiO_2)$ , and to investigate the initial cell response to it.

*Materials and Methods:* The ideal concentration of ammonium hydrogen fluoride  $(NH_4F-HF_2)$  used in this study was determined by a static water contact angle assay. The ideal concentration of  $NH_4F-HF_2$  was 0.175%, and experimental disks were treated with this concentration. A pluripotent mesenchymal cell line, C2C12, was cultured on the disks in order to investigate cell attachment, morphology, and proliferation.

*Results:* Cell attachment after 30 minutes of culturing was significantly higher for the ultraviolet-irradiated, fluoridemodified anodized  $TiO_2$  (p < .05), and the simultaneous scanning electron microscope observation showed a rather flattened and extended cell morphology. The proliferation rate after 24 hours was also significantly higher for the fluoridemodified anodized  $TiO_2$ .

*Conclusion:* Fluoride chemical modification enhances the hydrophilic property of the anodized  $TiO_2$  and improves the initial cell response to it.

KEY WORDS: ammonium hydrogen fluoride, anodization, hydrophilicity, titanium, ultraviolet irradiation

The anatase titanium dioxide  $(TiO_2)$  surface is known to acquire photocatalytic properties under ultraviolet (UV) irradiation.<sup>1-3</sup> The mechanisms of the decomposition of various organic compounds by photocatalysts have been well described.<sup>4</sup> As a result of those studies, photocatalytic surfaces are now thought to have

© 2007, Copyright the Authors Journal Compilation © 2007, Blackwell Publishing

DOI 10.1111/j.1708-8208.2007.00061.x

various qualities such as bactericidal activity,<sup>1,5</sup> deodorization capability,<sup>6</sup> decontamination capability,<sup>7</sup> and hydrophilicity.<sup>8</sup>

Photoinduced hydrophilicity was originally discovered by Wang and colleagues,<sup>9</sup> who demonstrated that a thin TiO<sub>2</sub> polycrystalline film made of anatase sol exhibited a dramatic decrease in the water contact angle, to  $0^{\circ} \pm 1^{\circ}$ , after UV irradiation. The UV irradiation of the photocatalyst theoretically creates surface oxygen vacancies at the bridging sites, resulting in the conversion of the relevant Ti<sup>4+</sup> sites to Ti<sup>3+</sup> sites, which is favorable for dissociative water adsorption.<sup>10</sup> These defects presumably influence the affinity of chemisorbed water for the surrounding sites, thereby forming hydrophilic domains.

In the field of implant dentistry, hydrophilicity is an important factor for the initial biological cascade of osseointegration. Several recent reports have focused on the hydrophilic profiles of surface-modified Ti implants.<sup>11–13</sup> A chemically cleaned microstructured

<sup>\*</sup>Division of Applied Prosthodontics, Nagasaki University Graduate School of Biomedical Sciences, Nagasaki, Japan; <sup>†</sup>Industrial Technology Center of Nagasaki, Nagasaki, Japan; <sup>‡</sup>Division of Prosthetic Dentistry, Nagasaki University Graduate School of Biomedical Sciences, Nagasaki, Japan; <sup>§</sup>Division of Oral Pathology and Bone Metabolism, Nagasaki University Graduate School of Biomedical Sciences, Nagasaki, Japan

Reprint requests: Dr. Takashi Sawase, Division of Applied Prosthodontics, Nagasaki University Graduate School of Biomedical Sciences, 1-7-1 Sakamoto, 852-8588, Nagasaki, Japan; e-mail: sawase@ nagasaki-u.ac.jp

surface increases the dynamic wettability of Ti implant surfaces and enhances the initial biological cell response. It has also been clarified by Buser and colleagues<sup>14</sup> that implants with hydrophilic properties enhance the initial bone apposition to the implant surface. Because it has been reported that changes in the physicochemical properties promote protein adsorption and further cell attachment through integrin-mediated mechanisms,<sup>15</sup> the hydrophilic TiO<sub>2</sub> surface is also speculated to first promote protein adsorption, and then to enhance cell behavior and bone apposition.

In our past study, we found that the commercially available TiUnite(tm) implant (Nobel Biocare AB, Göteborg, Sweden), which was created by anodization, shows photoinduced hydrophilicity after UV irradiation.<sup>16</sup> The contact angle significantly decreased from 44° to 11° upon UV irradiation, and the methylene blue degradation was also significant. However, we could not spot significant differences by histomorphometrical means between the ordinal TiUnite and the UV-irradiated TiUnite in animal experiments. We concluded that this may be because of the insufficient level of surface hydrophilicity, meaning that the low content of crystalline anatase was not enough to enhance bone regeneration. Therefore, it was hypothesized that further surface modification of the anodized TiO<sub>2</sub> in order to enlarge the crystalline anatase surface area would improve the hydrophilicity upon UV irradiation. It was further speculated that the improved hydrophilicity would naturally upturn the initial cell response, including cell attachment and proliferation, leading to enhanced bone apposition to the implant surface.

In this study, we focused our attention on fluoride as a means of modifying the anodized TiO<sub>2</sub> surface, because fluoride has been used in studies to improve the crystallinity of anatase for enhanced photocatalytic activity. Hattori and colleagues17,18 have stated that fluoride modification, the so-called F-doping of photocatalytic TiO<sub>2</sub>, resulted in an increase in anatase crystallinity. Yu and colleagues<sup>19</sup> have stated that fluoride ions not only suppress the formation of brookite, but also prevent the phase transition of anatase to rutile. They have also stated that the F-doped TiO<sub>2</sub> samples showed stronger absorption in the UV-visible range. This promising background motivated us to use fluoride as a possible enhancer for the photoinduced hydrophilicity and further observe the initial cell reactions to the fluoride-modified anodized titanium disk in terms of cell attachment, morphology, and proliferation.

#### MATERIALS AND METHODS

#### **Specimen Preparation**

Commercially pure Ti disks (grade 2, Furuuchi Co., Tokyo, Japan), 10 mm in diameter and 1 mm in thickness, were ground on a series of silicon carbide papers (320, 600, and 1,000 grit) and were anodized in an electrolytic solution consisting of  $1.5 \text{ M H}_2\text{SO}_4$ , 0.3 M H<sub>3</sub>PO<sub>4</sub>, and 0.3 M H<sub>2</sub>O<sub>2</sub> under direct constant current electrolysis at 3.0 A/dm<sup>2</sup> to a final voltage of 200 V for 10 minutes. Finally, the specimens were ultrasonically degreased in trichloroethylene for 15 minutes, followed by soaking in 95% ethanol for 15 minutes and distilled water for 15 minutes three times.

#### Ammonium Hydrogen Fluoride Treatment

The concentration of the NH<sub>4</sub>F-HF<sub>2</sub> that showed the highest hydrophilicity (tested range: 0 to 0.2%) was determined through contact angle analysis using a FACE contact angle analyzer (Kyowa Interface Science Co., Ltd., Asaka, Japan) in conjunction with the sessile drop technique. These measurements were carried out at room temperature in air with distilled water as the probe liquid. Liquid droplets (8  $\mu$ L) were deposited onto the sample surface at a rate of 8  $\mu$ L/s. Six each of the disk-shaped specimens were used for this analysis, and the contact angles reported here represent the averages of at least five measurements. The results are shown in Figure 1. The ideal concentration was 0.175%, and the disks treated with this concentration were used in the cell culture assay.

#### Surface Analysis

Micrographs of the anodized disks with or without the uppermost hydrophilic 0.175%  $NH_4F-HF_2$  treatment were taken using a scanning electron microscope (SEM) (S-3500N, Hitachi High-Tech Corp., Ibaragi, Japan). The surface roughness was analyzed using a color three-dimensional laser microscope (VK-8700, KEYENCE, Osaka, Japan). The centerline average roughness ( $R_a$ ) values for each disk were determined by averaging the values of five random areas per disk. The mean  $R_a$  values are an average of three disks for both groups.

## Cell Culture Assay

The pluripotent mesenchymal precursor C2C12 cell line was obtained from the Riken Gene Bank (Tsukuba,



Figure 1 The water contact angle of the  $NH_4F-HF_2$ -treated specimens, ranging from 0 to 0.2%. The optimum concentration was 0.175%.

Japan). The cells were cultured in  $\alpha$ -minimum essential medium ( $\alpha$ -MEM, Gibco Laboratories, Grand Island, NY, USA) supplemented with 10% fetal calf serum, streptomycin (100 µg/mL), penicillin (100 U/mL), and glutamine (2 mM) in an atmosphere of 100% humidity and 5% CO<sub>2</sub> at 37°C. Sub-confluent cultured cells were detached by trypsinization and were then plated on the following groups of disks, which were placed in 24-well polystyrene plates at a dilution of  $4 \times 10^4$  cells/mL: group 1 (anodized TiO<sub>2</sub> disks without UV irradiation), group 2 (anodized TiO<sub>2</sub> disks with UV irradiation for 24 hours), group 3 (anodized TiO<sub>2</sub> disks treated with 0.175% NH<sub>4</sub>F-HF<sub>2</sub> without UV irradiation), and group 4 (anodized TiO<sub>2</sub> disks treated with 0.175% NH<sub>4</sub>F-HF<sub>2</sub> with UV irradiation for 24 hours).

The cell morphology after 30 minutes of incubation was observed by SEM. The samples were washed twice with phosphate-buffered saline (PBS) and then washed in a 0.1 M sodium cacodylate buffer solution, postfixed with 2.5% glutaraldehyde/30 mM N-2-hydroxyethylpiperazine-N'-2-ethanesulfonic acid for 20 minutes, and finally dehydrated in an ascending series of ethanol. Each specimen was sputter coated with gold prior to SEM.

After 30 minutes of incubation, cell attachment was also evaluated as follows. The adherent cells were washed twice with PBS, fixed with 4% formaldehyde/PBS for 20 minutes, and nuclear stained with propidium iodide  $(50 \ \mu\text{g/mL})$  for 20 minutes. Five points for each disk

(n = 6, a total of 30 points for each group) were randomly selected, and the number of stained nuclei in an area of  $175 \times 140 \,\mu\text{m}$  was counted using a laser microscope (Axioskop 2, Carl Zeiss, Oberkochen, Germany) and Image J version 1.36b analyzing software (National Institutes of Health, Bethesda, MD, USA).

The proliferation of the cells was evaluated immunocytologically by the uptake of 5-bromodeoxyuridine (BrdU) at 24 hours after incubation. The cells were treated with 1% BrdU (Invitrogen, Carlsbad, CA, USA) for 2 hours prior to fixation with 70% ethanol, and permeabilized with 2.0 M HCl for 30 minutes, followed by treatment with 0.5% Tween-20 for 15 minutes. After the mentioned pretreatment procedures, the cells were treated with 1 µg/mL fluorescein isothiocyanateconjugated monoclonal mouse anti-BrdU (Biomeda, Foster City, CA, USA) for 30 minutes. The cells were further stained with propidium iodide (50  $\mu$ g/mL) for 20 minutes. The number of BrdU-positive cells was estimated using the method described in the cell attachment assay (randomly selected five points for each disk; n = 6; 30 points for each group), and the percentage of BrdU-positive cells relative to the number of cells stained with propidium iodide was used to calculate the cell proliferation.

# Statistical Analysis

All statistical analyses in the present study were performed with the KaleidaGraph software (Synergy Software, Essex Junction, VT, USA). The mean and SD values for the in vitro parameters were calculated. The average values were compared by one-way analysis of variance, followed by a post hoc Tukey-Kramer test with the value of statistical significance set at the 0.05 level.

#### RESULTS

#### Photoinduced Hydrophilicity

The water contact angles of the  $NH_4F-HF_2$ -treated specimens ranging from 0 to 0.2% are shown in Figure 1. The optimum concentration that showed the highest hydrophilicity was 0.175%. Although  $NH_4F-HF_2$  concentrations higher or lower than 0.175% showed improved hydrophilicity compared to the nontreated specimens, the 0.175%  $NH_4F-HF_2$  treatment showed significantly highest hydrophilicity among any other concentrations tested.

The contact angle measurements indicated that groups 1 and 3 had hydrophobic surfaces, with an



**Figure 2** Scanning electron microscope micrographs of the (A) ordinal anodized disk and the (B) NH<sub>4</sub>F-HF<sub>2</sub>-treated anodized disk. The corresponding surface roughness values are shown.

average contact angle of 45.5° and 47.3°, respectively. As reported in our past study, the UV-irradiated anodized surface (group 3) became hydrophilic, with an average contact angle of 11.5°. Furthermore, group 4 showed an improved contact angle of 4.2°.

## Surface Characteristics

SEM micrographs of the tested substrates can be observed in Figure 2. A rather smooth structure could be observed for the NH<sub>4</sub>F-HF<sub>2</sub>-treated anodized disks as compared to the nontreated anodized disks. The mean  $R_a$  values (SD) of the anodized and NH<sub>4</sub>F-HF<sub>2</sub>-treated anodized disks were 0.94 (0.04) and 0.82 (0.06), respectively. The NH<sub>4</sub>F-HF<sub>2</sub> treatment seemed to have smoothened the anodized disks.

## Cell Culture Assay

The cell morphology after 30 minutes of incubation can be observed in Figure 3. Groups 1 to 3 showed a rather round morphology with filopodia extensions (see



**Figure 3** Morphological scanning electron microscope observations of the cultured cells after 30 minutes of incubation: (A) group 1, (B) group 2, (C) group 3, and (D) group 4.



**Figure 4** Cell attachment and cell proliferation analyses. *A*, Cell attachment after 30 minutes of incubation. *B*, Cell proliferation evaluated based on the 5-bromodeoxyuridine uptake at 24 hours (mean  $\pm$  SD; \**p* < .01).

Figure 3, A–C). In contrast, the morphology for group 4 showed flattened seeded cells with numerous omnidirectional lamellipodia extensions (see Figure 3D).

The results of the cell attachment assay are shown in Figure 4A. The means (SD) of the attachment numbers were as follows: group 1: 7.35  $(2.45) \times 10^2$ /mm<sup>2</sup>; group 2: 8.08  $(2.45) \times 10^2$ /mm<sup>2</sup>; group 3: 9.67  $(3.35) \times 10^2$ /mm<sup>2</sup>; and group 4: 12.7  $(3.47) \times 10^2$ /mm<sup>2</sup>. There was no significant difference among groups 1 to 3, whereas the number of attached cells for group 4 was significantly higher compared to that for the other groups.

The results of the cell proliferation assay are shown in Figure 4B. The means (SD) of the proliferation rates were as follows: group 1: 30.3% (4.6); group 2: 37.5% (7.1); group 3: 35.0% (5.9); and group 4: 47.2% (7.6). Cell proliferation after 24 hours of incubation indicated a significantly higher proliferation rate for group 4 compared to that for the other groups, and no significant difference could be observed between groups 1, 2, and 3.

#### DISCUSSION

The central finding of this investigation was that the fluoride modification of the anodized titanium improved its photoinduced hydrophilicity, resulting in a better initial cell response. After a short time of culturing, the mesenchymal cells showed a significant increase in cell attachment. The corresponding cell morphology was flat, with pseudopodial extentions. In addition, the proliferative activity was significantly accelerated after 24 hours.

The water contact angle analysis showed that the anodized surface became hydrophilic after UV irradia-

tion. However, this level of hydrophilicity did not induce a more prominent cell response. On the other hand, the fluoride-treated anodized titanium after UV irradiation showed further improved hydrophilicity.

The SEM examination revealed a rather flattened structure after fluoride modification, a result corroborated by topographical measurements. However, neither the electron spectroscopic surface analysis for the chemical analysis nor the X-ray diffraction analysis showed any difference in the crystal structure before and after fluoride modification (data not shown). The overall mechanism through which the photoinduced hydrophilicity improved after fluoride modification remains unclear at this point.

Although the mechanism remains to be elucidated, the improved hydrophilicity did enhance the initial cell response. One key factor may be the surface energy intensified by the increased hydrophilicity. There are reports stating that hydrophilic surfaces cause an augmentation of the surface energy. Rupp and colleagues<sup>12</sup> have reported that a highly energized microstructured Ti surface acquired higher biological performance in vitro. Buser and colleagues<sup>14</sup> have also reported that inorganic molecules, such as calcium and phosphate ions, and, equally importantly, organic molecules, such as proteins, lipoproteins, and peptides, adsorb onto the hydroxylated/hydrated TiO<sub>2</sub> surface when exposed to the patient's blood, and they have speculated that this phenomenon involves electrostatic interactions.

In addition, the remnant fluoride may have acted in synergy with the hydrophilicity to intensify the cell response. Numerous studies report that fluoride may act primarily on osteoprogenitor cells, undifferentiated osteoblasts, and/or mesenchymal stem cells which synthesize an abundance of growth factors, rather than stimulating the proliferation of highly differentiated osteoblasts.<sup>20–23</sup> Furthermore, Ellingsen<sup>24</sup> has stated that fluoride may be the key inductive factor in the transformation of undifferentiated precursor cells into osteoblasts.

Judging comprehensively, the enhanced initial cell attachment and proliferation seen in the present study were speculated to be results of numerous factors, as indicated earlier. Hence, it may be difficult to clarify the mechanism that caused this enhancement if we focus only on the hydrophilicity. However, the results of this in vitro study are promising, and the in vivo effects involved in the possible acceleration of osseointegration will be discussed in future studies.

# CONCLUSIONS

The fluoride chemical modification of the anodized  $TiO_2$  disk surface significantly enhanced its photoinduced hydrophilicity. Although the full clarification of the mechanism involved is yet to be made, the modification clearly and significantly enhanced the initial cell attachment and subsequent proliferation activities.

# ACKNOWLEDGMENT

This study was supported by a Grant-in-Aid for Scientific Research (B) from the Japan Society for the Promotion of Science (#18390520).

# REFERENCES

- Suketa N, Sawase T, Kitaura H, et al. An antibacterial surface on dental implants, based on the photocatalytic bactericidal effect. Clin Implant Dent Relat Res 2005; 7:105–111.
- McMurray TA, Byrne JA, Dunlop PSM, McAdams ET. Photocatalytic and electrochemically assisted photocatalytic oxidation of formic acid on TiO<sub>2</sub> films under UVA and UVB irradiation. J Appl Electrochem 2005; 35:723–731.
- Xie YB, Li XZ. Preparation and characterization of TiO<sub>2</sub>/Ti film electrodes by anodization at low voltage for photoelectrocatalytic application. J Appl Electrochem 2006; 36:663– 668.
- Fujishima A, Tata NR, Donald AT. Titanium dioxide photocatalysis. J Photochem Photobiol C Photochem Rev 2000; 1:1–21.
- 5. Nakamura H, Tanaka M, Shinohara S, Gotoh M, Karube I. Development of a self-sterilizing lancet coated with a tita-

nium dioxide photocatalytic nano-layer for self-monitoring of blood glucose. Biosens Bioelectron 2006. (In press)

- Dalton JS, Janes PA, Jones NG, Nicholson JA, Hallam KR, Allen GC. Photocatalytic oxidation of NO<sub>x</sub> gases using TiO<sub>2</sub>: a surface spectroscopic approach. Environ Pollut 2002; 120:415–422.
- Kus M, Gernjak W, Ibanez PF, Rodriguez SM, Galvez JB, Icli S. A comparative study of supported TiO<sub>2</sub> as photocatalyst in water decontamination at solar pilot plant scale. J Solar Energy Eng 2006; 128:331–337.
- Nakajima A, Koizumi S, Watanabe T, Hashimoto K. Effect of repeated photo-illumination on the wettability conversion of titanium dioxide. J Photochem Photobiol A 2001; 146:129–132.
- 9. Wang R, Hashimoto K, Fujishima A, et al. Light-induced amphiphilic surfaces. Nature 1997; 388:431–432.
- Guillemot M, Porté C, Labrugère C, Baquey CH. Ti<sup>4+</sup> to Ti<sup>3+</sup> conversion of TiO<sub>2</sub> uppermost layer by low-temperature vacuum annealing: interest for titanium biomedical applications. J Colloid Interface Sci 2002; 255:75–78.
- Valagao Amadeu do Serro AP, Fernandes AC, de Jesus Vieira Saramago B, Norde W. Bovine serum albumin adsorption on titania surfaces and its relation to wettability aspects. J Biomed Mater Res 1999; 46:376–381.
- Rupp F, Scheideler L, Rehbein D, Axmann D, Geis-Gerstorfer J. Roughness induced dynamic changes of wettability of acid etched titanium implant modifications. Biomaterials 2004; 25:1429–1438.
- Rupp F, Scheideler L, Olshanska N, de Wild M, Wieland M, Geis-Gerstorfer J. Enhancing surface free energy and hydrophilicity through chemical modification of microstructured titanium implant surfaces. J Biomed Mater Res A 2006; 76:323–334.
- Buser D, Broggini N, Wieland M, et al. Enhanced bone apposition to a chemically modified SLA titanium surface. J Dent Res 2004; 83:529–533.
- Kilpadi KL, Chang PL, Bellis SL. Hydroxyapatite binds more serum proteins, purified integrins, and osteoblast precursor cells than titanium or steel. J Biomed Mater Res 2001; 57:258–267.
- Sawase T, Jimbo R, Wennerberg A, Suketa N, Tanaka Y, Atsuta M. A novel characteristic of porous titanium oxide implants. Clin Oral Implants Res 2007. (Accepted for publication)
- 17. Hattori A, Yamamoto M, Tada H, Ito S. A promoting effect of  $NH_4F$  addition on the photocatalytic activity of sol–gel TiO<sub>2</sub> films. Chem Lett 1998; 27:707–708.
- Hattori A, Tada H. High photocatalytic activity of F-doped TiO<sub>2</sub> film on glass. J Sol-Gel Sci Tech 2001; 22:47–52.
- Yu JC, Yu J, Ho W, Jiang Z, Zhang L. Effects of F-doping on the photocatalytic activity and microstructures of nanocrystalline TiO<sub>2</sub> powders. Chem Mater 2002; 14:3808– 3816.

- Bellows CG, Heersche JN, Aubin JE. The effects of fluoride on osteoblast progenitors in vitro. J Bone Miner Res 1990; 5(Suppl 1):S101–105.
- Kassem M, Mosekilde L, Erikssen EF. 1,25-dihydroxyvitamin D3 potentiates fluoride-stimulated collagen type I production in cultures of human bone marrow stromal osteoblast-like cells. J Bone Miner Res 1993; 8:1453–1458.
- 22. Kassem M, Mosekilde L, Erikssen EF. Effects of fluoride on human bone cells in vitro: differences in responsiveness

between stromal osteoblast precursors and mature osteoblasts. Eur J Endocrinol 1994; 130:381–386.

- Cooper LF, Zhou Y, Takebe J, et al. Fluoride modification effects on osteoblast behavior and bone formation at TiO<sub>2</sub> grit-blasted c.p. titanium endosseous implants. Biomaterials 2006; 27:926–936.
- 24. Ellingsen JE. The development of a bone regeneration promoting implant surface. Appl Osseointegration Res 2006; 5:18–23.

Copyright of Clinical Implant Dentistry & Related Research is the property of Blackwell Publishing Limited and its content may not be copied or emailed to multiple sites or posted to a listserv without the copyright holder's express written permission. However, users may print, download, or email articles for individual use.