DISCUSSION PAPER

In vitro and in vivo studies on the toxicity of dental resin components: a review

Michel Goldberg

Received: 17 April 2007 / Accepted: 31 October 2007 / Published online: 27 November 2007 © Springer-Verlag 2007

Abstract In vitro and in vivo studies have clearly identified that some components of restorative composite resins, adhesives, and resin-modified glass ionomer cements are toxic. The mechanisms of cytotoxicity are related firstly to the short-term release of free monomers occurring during the monomer-polymer conversion. Secondly, long-term release of leachable substances is generated by erosion and degradation over time. In addition, ion release and proliferation of bacteria located at the interface between the restorative material and dental tissues are also implicated in the tissue response. Molecular mechanisms involve glutathione depletion and reactive oxygen species (ROS) production as key factors leading to pulp or gingival cell apoptosis. Experimental animal approaches substantiate the occurrence of allergic reactions. There is a large gap between the results published by research laboratories and clinical reports.

Keywords Composite resin · Resin-modified glass ionomer cement · Adhesive · Free monomers · HEMA · TEGDMA · Free radicals · Cytotoxicity · Glutathione · Allergy · Mutagenicity

Do dental materials fulfill the clinical requirements?

Out of the 290-million cavities restored each year in the United States, 200 million are replaced for failed restorations [4]; the use of amalgam as restorative material is

M. Goldberg (⊠)
Faculté de Chirurgie Dentaire, University Paris 5,
EA 2496, 1, rue Maurice Arnoux,
92120 Montrouge, France
e-mail: mgoldod@aol.com

decreasing, whereas the number of tooth-colored composites and resin-modified glass ionomer cements (RM-GIC) restorations is increasing. Despite dentistry becoming gradually a sophisticated biomedical discipline, one of its Achilles' heels seems to be the restorative materials that are responsible for such an unacceptable high proportion of failures. Despite the fact that composites and RM-GIC have improved their physico-chemical properties, their intrinsic toxicity remains high, at least when they are evaluated in vitro. In addition, due to the fact they are tooth-colored, dental practitioners use less other restorative materials such as silver amalgam. Secondary caries is the most frequent reason for replacing restorations. A clear-cut explanation for that is that resins shrink during polymerization, leaving a gap colonized by bacteria between the material and the cavity walls, and the so-called hybrid layer does not exclude bacterial penetration [15]. This contributes to the development of secondary caries. In addition, unbound free monomers are excellent substrates for cariogenic bacteria [32]. Other reasons for failures are either mechanical, hypersensitivity, or both, and a few teeth can only be cured by endodontic treatment [9, 49]. Altogether, there is a need for the reevaluation of the physicochemical and biological properties of materials currently used in restorative dentistry that apparently do not fulfill the requirements of safety and longevity.

During the last few decades, the enthusiasm was great for resin composite and resin-modified glass ionomer cements that are tooth-colored materials considered as possible substitutes to mercury-containing silver amalgam filling. Ecological and esthetic considerations lead to the decrease of a material with long standing clinical experience to the profit of resin-containing materials with a partially very short "market life span" (only months sometimes). It is clear that defective mechanical properties such as shrinkage due to dimensional changes during resin polymerization and poor resistance to abrasion have decreased the initial eagerness.

Three comments should be done. Firstly, unbound monomers favor bacteria proliferation, especially the microorganisms implicated in caries formation. Therefore, they contribute to the development of secondary caries. Secondly, cellular and molecular mechanisms of cytotoxicity are initiated by the monomers, leading to pulp alteration and retraction of the gingival margin [29, 57]. Thirdly, local and systemic allergic-related reactions have been reported [34]. In this context, between 0.7% and 2% of patients and dental practitioners display allergic reactions [10, 35, 50, 55].

A number of in vitro and animal studies clarify the mechanisms of adverse reactions. In contrast, there is a need for more well-controlled unbiased clinical reports. Either there is no harmful reaction or they are not reported. In any case, there is an enormous gap between in vitro and in vivo studies. Apparently, the follow-up of restorative materials do not provide information on the actual physiopathological status of the pulp, probably because the methods used by clinicians are rather crude and not accurate enough. The reasons for the discrepancies between the two groups of reports are not yet clear. The link between the work going on in laboratories and the restorative therapies is missing up to now. However, it would be surprising that the harmful effects that are well identified in laboratory studies, and reviewed in this paper, have no clinical consequences. In the next future, we might face major problems in terms of public health. In the present article, in vitro data and in vivo animal studies will review the adverse effects of resin composites, RM-GIC, and dental adhesives.

Composition of composite resins and resin-modified GIC

Composite resins are tooth-colored filling materials composed by a mixture of (1) an organic polymerizable matrix, (2) particulate ceramic reinforcing fillers, (3) molecules promoting or modifying the polymerization reaction, and (4) silane coupling agent connecting the fillers and the organic matrix. The filler is inorganic in nature, formed by quartz, borosilicate, lithium-aluminum-silicate glasses, and amorphous silica. The terms of "all-purpose" or "universal", "anterior" or "posterior" describe the intended use of composites by dental practitioners. They are better than "conventional" or "traditional", "microfilled" or "hybrid", "flowable" or "packable", which were used formerly. This recent terminology does not refer to the particle filler size and is inappropriate for the characterization of the type of material, considerable variations of size, shape, and volume of the filler occurring within and between materials. In addition, fillers do not seem to play a major role in the biocompatibility of the material. The organic polymerized matrix seems to be responsible for most of the reported undesirable effects.

Many in vitro studies have shown that the polymerization reaction that produces the cross-linked polymer matrix from the dimethacrylate resin monomer is never complete and adverse reactions are due to the release of nonpolymerized monomers such as triethylene glycol methacrylate (TEG DMA) or 2-hydroxy-ethyl-methacrylate (HEMA). Unbound free monomers seem to be directly responsible for the cytotoxicity of resin composites on pulp and gingival cells, and they are probably also implicated in the allergic potential of the material [19]. Recent progress of dental composites did not change the occurrence of cytotoxic effects, and in this context, similar toxic levels were obtained with packable and nonpackable dental composites [22].

Conventional glass ionomer cements (GIC) are composed of glass, e.g., Ca-Al-F-silicate-glass, and poly (acrylic) carbonic acids. They have a good biocompatibility [29]. Along this line, rat first maxillary molars were submitted to cavity preparation and filled with Fuji IX GIC. After 8 days, a moderate inflammatory reaction was seen in the pulp, which was totally resolved at day 30 [72]. However, to improve mechanical properties and facilitate clinical handling, resin-modified glass ionomer cements (RM-GIC) have been developed by the industry. RM-GICs contain poly(acrylic)acids, photocuring monomers (HEMA) or a photocuring side chain grafted onto the poly(acrylic) acid and an ion-leaching glass. GICs have been also combined with resin composite components, such as dimethacrylates, benzophenone, and camphoroquinone, giving rise to a group of mixed restorative materials called compomers and RM-GICs. These materials and dentin bonding agents have now been studied and shown to be cytotoxic for pulp and gingival cells [58, 78].

Mechanisms of cytotoxicity

Although unbound free monomers released by dental resins during polymerization and later are considered by a majority of authors to be responsible for the cytotoxic effects, additional mechanisms have been also proposed.

Short-term release of free monomers occurring during the monomer–polymer conversion

Unbound monomers and/or additives are eluted by solvents or polymer degradation within the first hours after initial polymerization. The release is due to defective photopolymerization, thermal, mechanical or chemical factors. Approximately 15–50% of the methacrylic groups remain unreacted [19]. Due to the efforts of the industry, the percentage of unbound monomers has been decreased during the past 10 years, but the problem is still not eradicated. Up to now, there is no total conversion during polymerization. It may be expected that at the end of initial polymerization, most of the monomers will react with the polymer network and the quantity of residual monomers is less than a tenth of the remaining methacrylic groups, which, therefore, have been evaluated as no more than 1.5-5%. However, this is enough to contribute to major cytotoxic effects [75]. The reaction is also dependent on dentin permeability and residual dentin thickness [8]. The residual dentin layer absorbs unbound monomers and, therefore, contributes to the decrease in the cytotoxicity of the material, but this parameter is not directly under the control of the dental surgeon, although the formation of reactionary dentin may be stimulated by preparative steps. Dentin permeability may also be modified by calcium/phosphate precipitation in the lumen of the tubules leading to sclerotic dentin formation. It has also been shown that the surface of composite resins exposed to oxygen during curing produces a nonpolymerized surface layer containing formaldehyde, which by itself is an additional factor of cell toxicity [64].

Monomers have been identified in dental composites eluates by gas and liquid chromatography/mass spectrometry. A considerable concentration of the comonomer triethyleneglycol-dimethacrylate (TEGDMA) and minor concentrations of the basic monomers bisphenol-A glycidyldimethacrylates (Bis-GMA) and UDMA and the comonomer HDDMA have been detected with these methods [28, 74]. The comonomer TEGDMA and the photostabilizer 2-hydro-4-methoxybenzophenone (HMBP) are cytotoxic and inhibit cell growth, but the most crucial consequence is that the intracellular glutathione level is decreased to $85\pm15\%$ by TEGDMA [17, 18, 75–77].

In vitro evaluation of the cytotoxicity of 35 dental resin composite monomers/additives indicates moderate to severe cytotoxic effects [28]. The results vary according to the material tested, but also they are strongly dependent on the cells used for testing. For example, human periodontal ligament and pulp fibroblasts are more sensitive than 3T3 and gingival fibroblasts [28]. With the exception of very few reports, there is a general consensus that resin-containing restorative materials are cytotoxic [25, 26, 64], especially after mixing.

At early intervals, resin-containing materials are more cytotoxic than at later intervals. However, long-term effects should also be taken into consideration.

Leachable substances generated by erosion and degradation over time

The chemical characteristics of leachable substances determine the diffusion through the polymer network. Leachable components are released due to degradation or erosion over time. Chemical degradation is caused by hydrolysis or enzymatic catalysis. Unspecific esterases and human salivaderived esterase may readily catalyze the biodegradation of commercial resinous materials [24, 26, 38]. Interactions between resin monomers and commercial composite resins with human saliva-derived esterases and pseudocholinesterase occur in the oral cavity and they contribute to the degradation of composite resins. Incubated in vitro with cholesterol esterase for 8, 16, and 32 days, resin composites release 2,2-bis [4(2,3-hydroxypropoxy)-phenyl]propane (bis-HPPP) and TEGMA. Depending on the material (lower filler vs higher filler composite), and consequently, on the matrix/filler ratio, lower or higher amounts of bis-HPPP and TEGMA are produced between 0 and 8 days [71].

Water or other solvents enter the polymer, leading to the release of biodegradation products, namely, oligomers and monomers. This form of erosion leads to weight loss of the polymer. Softening of the Bis-GMA matrix allows the solvents to penetrate more easily and expand the polymer network, a process that facilitates the long-term diffusion of unbound monomers [20, 21].

Release of ions

Resins and RM-GIC release ions such as fluoride, strontium, and aluminum. Some ions, such as fluoride, are expected to be beneficial and reduce the development of secondary caries. Presumably, the fluoride content of toothpastes and nutriments reload the material, so that the resins or RM-GICs do not become porous. Other ions are implicated in the color of the restorative material, and these metal elements may interfere with the biocompatibility of the resin because they are implicated in the Fenton reaction producing reactive oxygen species (ROS) that are cytotoxic. The concentration of F^- and Sr^{2+} is too low to be cytotoxic. In contrast, Cu^{2+} , Al^{3+} , and Fe^{2+} are present in toxic concentrations. The cytotoxic cascade was shown to be enhanced by metals, such as aluminum and iron, present in various amounts in composite resins and RM-GIC [75–77].

The role of bacteria at the interface between the restorative material and dental tissues

The presence, and consequently, the effects of bacteria located at the interface between the resin and the dental tissues probably constitute important factors [32]. EGDMA and TEDGMA promote the proliferation of cariogenic microorganisms such as *Lactobacillus acidophilus* and *Streptococcus sobrinus*. As a confirmation, TEDGMA stimulates the growth of *S. mutans* and *S. salivarius* in a pH-dependent manner [42]. This provides an explanation for the secondary caries lesions that develop beneath resin-

containing restorative materials. In addition, bacterial exotoxins have noxious effects on pulp cells after diffusion throughout dentin tubules.

For years, some publications refuted any direct cytotoxic effects of the resin monomers upon the dental pulp and laid the blame on bacterial contamination [5, 6]. This is still a matter of controversy and a few reports still consider that the pulp reaction to adhesive systems is generally minimal [51, 52]. They incriminate the colonization by bacteria of the wide interface between the composite (or adhesive) and cavity walls. Bacteria may produce acids that can be responsible for the pulp reaction [5, 6]. This was considered true in the early 1980s when important volume shrinkage followed chemo-polymerization and produced gaps wider than 10 µm [6]. This interval was decreased by the layerby-layer photopolymerization technology. Improvements of resin-containing materials have reduced the shrinkage. New adhesive technologies lead to the formation of a hybrid layer and diminish the interface to less than 1 μ m [33]. However, this is still a large gap for many microorganisms such as lactobacilli that are less than 0.1 µm in diameter, and therefore, the microbial parameter cannot be ignored. Some authors have emphasized the importance of hemorrhage control and its interference with bacterial contamination [13]. However, the major issues today seem to be the short-term and long-term release of unbound toxic free monomers [25, 26, 75] rather than the release of acids and toxins by bacteria.

Molecular mechanisms of cytotoxicity: recent data

For more than 10 years, it is known that resin composites, dentin bonding components, and RM-GIC are cytotoxic. HEMA, TEGDMA, and UDMA have been incriminated [58]. Lefebvre et al. [46] have analyzed the action of TEGDMA, dimethylaminoethyl I metacrylate (DMAEFMA) on oral epithelial cells. It inhibits cell growth and total polar lipid synthesis. Even after polymerization, dental resins may elute into the immediate environment unbound monomers that alter various cell metabolic processes [27, 48, 75–77]. Other biological parameters have been studied, but their importance still needs to be established. Along these lines, HEMA and TEGDMA suppress heat shock protein 72 (HSP 72) expression in human monocytes [53]. TEGDMA induces mitochondrial damage [48]. The cytotoxicity of dentin-bonding resins seems also to be associated with defective intracellular tyrosine phosphorylation [39].

The exposure time and interactions between dentinbonding components are important parameters depending on the type of cells studied. TEGDMA is about twofold to fivefold more toxic than HEMA for pulmonary cells [41]. Intracellular glutathione level is decreased by TEGDMA within the first 2–6 h after setting [18]. At a TEGDMA concentration of \leq 2.5 mM, a regular reincrease is observed; whereas at higher concentrations, a continuous depletion occurs, concomitant with a significant decrease of cell viability.

HEMA is released from light-cured or RM-GIC and compomer cements [31]. Intracellular tyrosine phosphorylation is inhibited by HEMA and not by TEGDMA [39]. Chang et al. [11] have shown that HEMA induces cell growth inhibition and cycle perturbation; indeed, the arrest of cell S–G phases. The G_2/M and S phases arrest, glutathione depletion, and ROS production are key factors leading to cell apoptosis.

TEGDMA monomers released from dental resins induce in vitro a concentration-dependent and variable cytotoxic effect. Toxic concentration 50 (TC50) was obtained with 1.2±0.9 and 2.6±1.1 mM of TEGDMA for gingival and pulp fibroblasts, respectively. The depletion of glutathione due to the leaching of monomers starts at 15-30 min and is almost complete at 4-6 h. As a valuable demonstration of the importance of this mechanism, antioxidants such as Trolox, ascorbate, and N-acetylcysteine (NAC) prevent the TEGDMA-induced toxicity while GSH depletion is partially inhibited. Trolox, preventing the cell damages mediated by resin-containing dental restorative materials, inhibits the production of ROS that occurred after 3-4 h incubation in the presence of TEGDMA. Ascorbate increases, in a dose-dependent manner, the toxic effects of the eluates (additional 17-24% depletion of glutathione). D-mannitol neutralizes the toxic effect of ascorbate [70, 73, 76, 77]. The decreased toxicity of free monomers by these antioxidative agents paves the way for clinical attempts to reduce the potential noxious effects of resin-containing dental materials.

We recently reported that TEGDMA inhibits and potentiates glutathione transferase P1 (GSTP1) at high and low concentrations. Isoforms of GSTP1 have been identified in gingival fibroblasts, and depending on the phenotype, the reaction to TEGDMA varies. Cells of the GSTP1 *A/*A group and *A/*B variant show a weak inhibition and no significant difference between the two groups of cells. In contrast, the toxic dose 50 (TD50) value for *B/*B was significantly lower, and therefore, this isoform of GSTP1 may be less effective than *A/*A in detoxifying TEGDMA. These data suggest that GSTP1 polymorphism may be involved in the interindividual susceptibility to TEGDMA cytotoxicity [47]. Once confirmed on a greater scale, these data may contribute to the identification of a group of patients that are more susceptible than the rest of the population to present harmful reactions to resin monomers.

Local and general toxicity and mutagenic effects

In vitro studies

Cytotoxicity tests involve the evaluation on cell cultures of enzyme activities, membrane integrity, alteration of cell morphology, determination of cell growth inhibition, and determination of the effective dose that cause 50% reduction of cell proliferation (ED50). Counting surviving cells (TC50=50% reduction of cell survival), measurement of proliferation rates, synthesis of cellular macromolecules, and determination of enzyme activities are the most used and recognized indicators. A widely used method is the MTT test, although succinic dehydrogenase (SDI) and alkaline phosphatase responses have also been used [12]. Photopolymerized standardized cylinders of composite resin or RM-GIC, prepared according to the manufacturer's instructions, are incubated in culture medium. After 48 h of incubation, cells are incubated with or without (group control) the biomaterial eluates. Conventional and resin-modified GIC toxicity studies evaluated with the MTT test suggest that RM-GICs are more toxic than conventional GIC [45]. Depending on the cell lines used and the method of evaluation, the results may vary [80]. As an example, human pulp fibroblasts (not cloned) and human gingival fibroblasts tested with the MTT test and lactate dehydrogenase activity assay (LDH) gave different results, and MTT was more sensitive than LDH [36]. Despite methodological differences, altogether, the results underline the cytotoxic effects of the monomers released by resin-containing restorative materials.

TEGDMA is hydrophilic and interferes with oral tissues. The compound can penetrate membranes and reacts with intracellular molecules. Specifically, glutathione–TEGDMA adducts are formed, a mechanism reducing cellular detoxifying potency [27]. Significant toxic effects of TEGDMA and HEMA on glucogenesis were reported on isolated rat kidney tubules, although less toxic than the effects of mercuric chloride or methylmercury chloride [59]. Synergistic effects of H₂O₂ from dental bleaching compounds and monomers released by dental composites lead to increased toxicity on kidney cells [23]. Using the release of LDH as a biological indicator, toxicity was also reported in confluent alveolar epithelial lung cell lines in vitro [60].

Evaluation of the mutagenicity has shown that TEGDMA causes large DNA deletions in mammalian cells (genotoxicity) [68, 70]. TEGDMA, HEMA, and GMA induce an increase of the number of mutants by a factor of 2 to 8 [67] and the formation of micronuclei [69]. Using the Comet assay (alkaline single cell microgel electrophoresis assay), TEGDMA, UDMA, and Bis-GMA induce significant but minor enhancement of DNA migration, a possible sign for limited genotoxic effects [43]. More recent data

give evidence of a possible risk factor for tumor initiation in human salivary glands [44].

In vivo experimental studies

Direct pulp capping with adhesive resin-based composite leads generally to infection and necrosis [1, 66]. However, this is still a matter of controversy, and a few authors still believe that a better sealing of the restoration will prevent bacteria contamination, and consequently, better healing of the exposed pulp [5, 52]. Mild to severe inflammatory response was observed in human pulps treated with Scotchbond Multi-purpose, and no mineralized tissue formation was detected [16]. The clearance, distribution, and elimination of TEGDMA has been extensively studied [61, 62]. About 4% of the ¹⁴C-TEGDMA injected in the jugular vein of guinea pigs was found in different tissues such as muscle, kidney, skin, blood, and liver after 24 h, whereas 61.9% was exhaled. Exhalation seems to be the major route of elimination [61]. Gastric, intradermal, and intravenous administration of ¹⁴C-TEGDMA establish that most is excreted in 1 day, and the peak equivalent TEGDMA level in mouse and guinea pig is 1,000-fold less than known toxic levels [62]. In a third publication, Reichl et al. [63] have shown that after the administration of the radioactive monomer either in the gastric tube or after intradermal injection, the uptake was almost completed within 1 day. Low fecal (<1%) and urine (about 15%) elimination was noted, whereas between 60% and 65% was exhaled. In addition, ¹⁴C-pyruvate seems to be formed as a toxic ¹⁴C-TEGDMA-intermediate. Confirming previous findings, despite the high doses administered in this experimentation, after 24 h, the doses found in tissues were 100,000-fold less than known toxic levels [63].

Studies in animals and humans have shown mild to severe inflammatory pulp reactions, leading in many cases to cell apoptosis, followed by severe pulp alteration [29].

Estrogenic effects

Estrogenic activity of three fissure sealants has been associated with bisphenol A dimethacrylate (BPA-DMA) rather than with Bis-GMA [79]. It was shown that BPA-DMA can be cleaved by unspecific esterases producing BPA, which then may elicit an estrogenic reaction in vitro [3, 65]. The total amount of TEGDMA released per tooth is in the order of 0.25 mg, most of the release occurring on the first day [30]. Adverse effects were denied by Nomura et al. [54], and in any case, the dose released is considered to be too low to have any consequence on patients [64]. Moving from in vitro to in vivo studies, leached components or bisphenol A administered intragastrically daily to female mouse display 54.5% reduction in the number of pregnancies vs 100% in control mice. An effect on the ovaries was also reported, BPA having adverse effects on the fertility and reproductive system in female mice [2]. However, a study involving sealants applied to human subjects shows no detectable bisphenol A in the blood serum and saliva after 24 h [24].

Allergic responses to dental resins

The results from the Norwegian National Dental Biomaterial Adverse Reaction Unit listed for 4 years of activity from 1993 to 1997 indicate that out of the 296 patients who had been patch tested with substances in dental materials, 23% were positive to gold, 28% to nickel, 9% to palladium, 6% to mercury, and 8% to one or more components of resin-based materials [81]. Skin and mucosal reactions are associated with dental materials [35]. Skin symptom or hand eczema caused by contact allergy, appearing as an eczema, has been evaluated in a nonselected population of patients as 12%, in contrast with 27% found in a dentist group, 2% being caused by acrylic resin materials [34]. Another report indicates that 28% of the dentists have contact allergy to nickel, perfumes, and other chemicals with diagnosed hand eczema. Seven percent of the dentists display skin symptom to resin-based materials. Allergy to methacrylate of dental personnel is below 1% [55, 56, 82], but around 2% in another investigation [50].

According to Hume and Gerzina [35], dermatoses are the most frequently diagnosed adverse responses, together with paresthesia of the fingertips and allergic pharyngitis. HEMA causes contact dermatitis, and induces irritation and delayed hypersensitivity when applied to the skin of guinea pigs [40]. After the placement of resin composite restoration for orthodontic treatment, a few cases of allergic response have been published with edema and vesiculation of the oral mucosa and lips. Case reports refer to severe dermatitis on the limbs, trunk, and face whereas allergic reactions (bronchospasm, whole body urticaria, and blistering of the face, ears, and lips) are related to the placement then removal of sealants containing TEGDMA.

In the oral cavity, lichenoïd reactions have been observed in close relationship with composites and GIC [7, 36, 37]. It is also possible that immune cells play a role in the pulp response. Mast cell density is increased by adhesive resins and GIC [14].

Conclusions

It is clear that resin-containing restorative materials release unbound free monomers, immediately after setting and later. These monomers are cytotoxic in vitro for pulp and gingival cells. Leaching of some ions seems also to be implicated in cell alterations. Depletion of glutathione, production of ROS, and a few other molecular mechanisms have been identified as key factors leading to apoptosis and/or pulp necrosis. In addition, resin monomers stimulate the development of cariogenic bacteria at the interface between the material and the walls of the cavity. Dental resins have no intrinsic antibacterial properties, but some additives may have this effect. However, monomers provide a good substrate for cariogenic bacterial strains. This may lead to the formation of secondary caries, and further to the long-term degradation of the polymers, two factors involved in the failure of the restoration.

It is surprising to note that there is a large gap between the numerous reports on in vitro adverse reactions, what has been established on allergy and dermatitis, and the clinical evaluation of composites, adhesives, and RM-GIC [64]. In view of all the problems identified mostly in vitro, there is a need for clinical studies establishing or refuting a correlation with the in vivo situation.

References

- Accorinte Mde L, Loguercio AD, Reis A, Muench A, de Araujo VC (2005) Adverse effects of human pulps after direct pulp capping with the different components from a total-etch, threestep adhesive system. Dent Mater 21:599–607
- Al-Hiyyasat AS, Darmani H, Elbetieha AM (2004) Leached components from dental composites and their effects on fertility of female mice. Eur J Oral Sci 112:267–272
- Arenholt-Bindslev D, Breinholt V, Preiss A, Schmalz G (1999) Time-related bisphenol-A content and estrogenic activity in saliva samples collected in relation to placement of fissure sealants. Clin Oral Investig 3:120–125
- Arnst C, Carey J (1998) Biotech bodies. Business Week July pp. 42–49
- Bergenholtz G (2000) Evidence for bacterial causation of adverse pulpal responses in resin-based dental restorations. Crit Rev Oral Biol Med 11:467–480
- Bergenholtz G, Cox CF, Loesche WJ, Syed SA (1982) Bacterial leakage around dental restorations and bacterial growth in cavities. J Oral Pathol 11:439–450
- Blomgren J, Axell T, Sandahi O, Jontell M (1996) Adverse reactions in the oral mucosa associated with anterior composite restorations. J Oral Pathol & Med 25:311–313
- Bouilliaguet S, Virgillito M, Wataha J, Ciucchi B, Holz J (1998) The influence of dentine permeability on cytotoxicity of four dentine systems, in vitro. J Oral Rehabil 25:45–51
- Burke FJ, Cheung SW, Mjör IA, Wilson NH (1999) Reasons for the placement and replacement of restorations in vocational training practices. Prim Dent Care 6:17–20
- Carmichael AJ, Gibson JJ, Walls AW (1997) Allergic contact dermatic to bisphenol-A-glycidyldimethacrylate (BIS-GMA) dental resin associated with sensitivity to epoxy resin. Br Dent J 183:297–298
- Chang H-H, Guo M-K, Kasten FH, Chang M-C, Huang G-F, Wang Y-L, Wang R-S, Jeng J-H (2005) Stimulation of glutathione

depletion, ROS production and cell cycle arrest of dental pulp cells and gingival epithelial cells by HEMA. Biomaterials 26:745–753

- Chen CC, Chen RC, Huang ST (2002) Enzymatic response of human deciduous pulpal fibroblasts to dental restorative materials. J Biomed Mater Res 60:452–457
- Cox CF, Hafez AA, Akimoto N, Otsuki M, Suzuki S, Tarim B (1998) Biocompatibility of primer, adhesive and resin composite systems on exposed and exposed pulps of non-human primate teeth. Am J Dent 11(Spec No):S55–S63
- 14. De Oliveira Mussel RL, De Sa Silva E, Monte Alto Costa A, Mandarim-De-Lacerda CA, (2003) Mast cells in tissue response to dentistry materials: an adhesive resin, a calcium hydroxide and a glass ionomer cement. J Cell Mol Med 7:171–178
- De Munck J, Van Landuyt K, Peumans M, Poitevin A, Lambrecht P, Braem M, Van Meerbek B (2005) A critical review of the durability of adhesion to tooth tissue: methods and results. J Dent Res 84:118–132
- Demarco FF, Tarquinio SB, Jargerf MM, de Araujo VC, Matson E (2001) Pulp response and cytotoxicity evaluation of 2 dentin bonding agents. Quintessence Int 32:211–220
- Engelmann J, Leyhausen G, Leibfritz D, Geurtsen W (2001) Metabolic effects of dental resin components in vitro detected by NMR sprectroscopy. J Dent Res 80:869–875
- Engelmann J, Leyhausen G, Leibfritz D, Geurtsen W (2002) Effects of TEGDMA on the intracellular glutathione concentration of human gingival fibroblasts. J Biomed Mater Sci 63:746–751
- Ferracane JL (1994) Elution of leachable components from composites. J Oral Rehabil 21:441–452
- Finer Y, Jaffer F, Santerre JP (2004) Mutual influence of cholesterol esterase and pseudocholinesterase on the biodegradation of dental composites. Biomaterials 25:1787–1793
- Finer Y, Santerre JP (2004) The influence of resin chemistry on a dental composite's biodegradation. J Biomed Mater Res 69A:233– 246
- Franz A, Konig F, Anglmayer M, Rausch-fan X, Gille G, Rausch WD, Lucas T, Sperr W, Schedle A (2003) Cytotoxic effects of packable and nonpackable dental composites. Dent Mater 19:382–392
- 23. Franz-Xaver R, Jürgen D, Kai K, Matthias F, Norbert K, Markus S, El-Mahdy K, Reinhard H (2003) Synergistic effects of H₂O₂ with components of dental restorative materials on glucogenesis in rat kidney tubules. Biomaterials 24:1909–1916
- 24. Fung EY, Ewoldsen NO, St Germain HA Jr, Marx DB, Miaw C-L, Siew C, Chou H-N, Gruninger MS, Meyer DM (2000) Pharmacokinetics of bisphenol A released from a dental sealant. J Am Dent Assoc 131:51–58
- Geurtsen W (1998) Substances released from dental resin composites and glass ionomer cements. Eur J Oral Sci 106:687–695
- Geurtsen W (2000) Biocompatibility of resin-modified filling materials. Crit Rev Oral Biol Med 11:333–355
- Geurtsen W, Leyhausen G (2001) Chemical–biological interaction of the resin monomer triethyleneglycoldimetacrylate (TEGDMA). J Dent Res 80:2046–2050
- Geurtsen W, Lehmann F, Spahl W, Leyhausen G (1998) Cytotoxicity of 35 dental resin composite monomers/additives in permanent 3T3 and three primary fibroblast cultures. J Biomed Mater Res 41:474–480
- Goldberg M, Stanislawski L, Bonte E, Daniau X, Bonte E, Daniau X, Lasfargues J-J (1999) Biocompatibility of glass-ionomer cements. In: Davidson CL, Mjor IA (eds) Advances in glass-ionomer cements, chapter 5. Quintessence Publishing, Chicago, pp 103–120
- Hamid A, Hume WR (1997) A study of component release from resin pit and fissure sealants in vitro. Dent Mater 13:98–102
- Hamid A, Okamoto A, Iwaku M, Hume WR (1998) Component release from light-activated glass ionomer and compomer cements. J Oral Rehabil 25:94–99

- 32. Hansel C, Leyhausen G, Mai UE, Geurtsen W (1998) Effects of various resin composite (co)monomers and extracts on two cariesassociated micro-organisms in vitro. J Dent Res 77:60–67
- 33. Hashimoto M, Ito S, Tay FR, Svizero NR, Sano H, Kaga M, Pashley DM (2004) Fluid movement across the resin-dentin interface during and after bonding. J Dent Res 83:843–848
- Hensten-Pettersen A (1998) Skin and mucosal reactions associated with dental materials. Eur J Oral Sci 106:707–712
- Hume WR, Gerzina TM (1996) Bioavailability of components of resin-based materials which are applied to teeth. Crit Rev Oral Biol Med 7:172–179
- 36. Issa Y, Watts DC, Brunton PA, Waters CM, Duxbury AJ (2004) Resin composite monomers alter MTT and LDH activity of human gingival fibroblasts in vitro. Dent Mater 20:12–20
- Issa Y, Duxbury AJ, Macfarlane TV, Brunton PA (2005) Oral lichenoid lesions related to dental restorative materials. Br Dent J 198:361–366
- Jaffer F, Finer Y, Santerre JP (2002) Interactions between resin monomers and commercial composite resins with human saliva derived esterases. Biomaterials 23:1707–1719
- 39. Kaga M, Noda M, Ferracane JL, Nakamura W, Oguchi H, Sano H (2001) The in vitro cytotoxicity of eluates from dentin bonding resins and their effect on tyrosine phosphorylation of L929 cells. Dent Mater 17:333–339
- Katsuno K, Manabe A, Kurihara A, Itoh K, Hisamitsu H, Wakumoto S, Yoshida T (1998) The adverse effect of commercial dentine-bonding systems on the skin of guinea pigs. J Oral Rehabil 25:180–184
- Kehe K, Reichl FX, Durner J, Walther U, Hickel R, Forth W (2001) Cytotoxicity of dental composite components and mercury compounds in pulmonary cells. Biomaterials 22:317–322
- Khalichi P, Cvitkovitch DG, Santerre JP (2004) Effect of composite resin biodegradation products on oral streptococcal growth. Biomaterials 25:5467–5472
- 43. Kleinsasser NH, Wallner BC, Harréus UA, Kleinjung T, Folwaczny M, Hickel R, Kehe K, Reichl F-X (2004) Genotoxicity and cytotoxicity of dental materials in human lymphocytes as assessed by the single cell microgel electrophoresis (comet) assay. J Dent 32:229–234
- 44. Kleinsasser NH, Schmid K, Sassen AW, Harréus UA, Staudenmaier R, Folwaczny M, Glas J, Reichl F-X (2006) Cytotoxic and genotoxic effects of resin monomers in human salivary gland tissue and lymphocytes as assessed by the single cell microgel electrophoresis (comet) assay. Biomaterials 27:1762–1770
- 45. Lan WH, Lan WC, Wang TM, Lee YL, Tseng WY, Lin CP, Jeng JH, Chang MC (2003) Cytotoxicity of conventional and modified glass ionomer cements. Oper Dent 28:251–259
- Lefebvre CA, Schuster GS, Rueggeberg FA, Tamareselvy K, Knoernschild KL (1996) Response of oral epithelial cells to dental resin components. J Biomater Sci Polym Ed 7:965–976
- 47. Lefeuvre M, Bourd K, Loriot M-A, Goldberg M, Beaune P, Périanin A (2004) TEGDMA modulates glutathione-S-transferase P1 activity in gingival fibroblasts. J Dent Res 83:914–919
- Lefeuvre M, Amjaad W, Goldberg M, Stanislawski L (2005) TEGDMA induces mitochondrial damage and oxidative stress in human gingival fibroblasts. Biomaterials 26:5130–5137
- Mjör IA, Jokstad A, Qvist V (1990) Longevity of posterior restorations. Int Dent J 40:11–17
- Munksgaard EC, Hansen EK, Engen T, Holm U (1996) Selfreported occupational dermatological reactions among Danish dentists. Eur J Oral Sci 104:396–402
- Murray PE, Windsor LJ, Hafez AA, Stevenson RG, Cox CF (2003a) Comparison of pulp responses to resin composites. Oper Dent 28:242–250
- Murray PE, Hafez AA, Smith AJ, Cox CF (2003b) Identification of hierarchical factors to guide clinical decision making for successful long-term pulp capping. Quintessence Int 34:61–70

- 53. Noda M, Wataha JC, Kaga M, Lockwood PE, Volkmann KR, Sano H (2002) Components of dentinal adhesives modulate heat shock protein 72 expression in heat-stressed THP-1 human monocytes at sublethetal concentrations. J Dent Res 81:265–269
- 54. Nomura Y, Ishibashi H, Miyahara M, Shinohara R, Shiraishi F, Arizono K (2003) Effects of dental resin metabolites on estrogenic activity in vitro. J Mater Sci Mater Med 14:307–310
- Örtengren U (2000) On composite resin materials—degradation, erosion and possible adverse effects in dentists. Swed Dent J Suppl 141:1–61
- 56. Örtengren U, Andreasson H, Karlsson S, Meddling B, Barregärd L (1999) Prevalence of self-reported hand eczema and skin symptoma associated with dental materials among Swedish dentists. Eur J Oral Sci 107:496–505
- 57. Peumans M, Van Meerbeek B, Lambrechts P, Vanherle G, Quirynen M (1998) The influence of direct composite addition for the correction of tooth form and/or position on periodontal health. A retrospective study. J Periodontol 69:422–427
- Ratanasthien S, Watnha JC, Hanks CT, Dennison JB (1995) Cytotoxic interactive effects of dentin bonding components on mouse fibroblasts. J Dent Res 74:1602–1606
- Reichl FX, Durner J, Mückter H, Elsenhans B, Forth W, Kunzelmann KH, Hickel R, Spahl W, Hume WR, Moes GW (1999) Effects of dental materials on glucogenesis in rat kidney tubules. Arch Toxicol 73:381–386
- 60. Reichl FX, Walther UI, Durner J, Kehe K, Hickel R, Kunzelmann KH, Spahl W, Hume WR, Benschop H, Forth W (2001a) Cytotoxicity of dental composite components and mercury compounds in lung cells. Dent Mater 17:95–101
- Reichl FX, Durner J, Kunzelmann KH, Hickel R, Spahl W, Hume WR, Moes GWH, Kehe K, Walther U, Forth W (2001b) Biological clearance of TEGDMA in guinea pigs. Arch Toxicol 75:22–27
- 62. Reichl FX, Durner J, Hickel R, Kunzelmann KH, Jewett A, Wang MY, Spahl W, Kreppel H, Moes GW, Kehe K, Walther U, Forth W, Hume WR (2001c) Distribution and excretion of TEGDMA in guinea pigs and mice. J Dent Res 80:1412–1415
- 63. Reichl FX, Durner J, Hickel R, Spah W, Kehe K, Walther U, Gempel K, Liebl B, Kunzelmann KH, Hume W (2002) Uptake, clearance and metabolism of TEGMA in guinea pigs. Dent Mater 18:581–589
- 64. Schmalz G (1998) The biocompatibility of non-amalgam dental filling materials. Eur J Oral Sci 106:696–706
- Schmalz G, Preiss A, Arenholt-Bindslev D (1999) Bisphenol-A content of resin monomers and related degradation products. Clin Oral Investig 3:114–119
- 66. Schuurs AHB, Gruythuysen RJM, Wesselink PR (2000) Pulp capping with adhesive resin-based composite vs.calcium hydroxide: a review. Endod Dent Traumatol 16:240–250
- Schweikl H, Schmalz G, Rackbrandt K (1998) The mutagenic activity of unpolymerized resin monomers in *Salmonella typhimurium* and V79 cells. Mutat Res 415:119–130

- Schweikl H, Schmalz G (1999) Triethylene glycol dimetacrylate induces large deletions in the hprt gene of V79 cells. Mutat Res 438:71–78
- Schweikl H, Schmalz G, Spruss T (2001) The induction of micronuclei in vitro by unpolymerized resin monomers. J Dent Res 80:1615–1620
- Schweikl H, Spagnuolo G, Schmaltz G (2006) Genetic and cellular toxicology of dental resin monomers. J Dent Res 85:870– 877
- Shajii L, Santerre JP (1999) Effect of filler content on the profile of released biodegradation products in microfilled bis-GMA/ TEGDMA dental composite resins. Biomaterials 20:1897–1908
- Six N, Lasfargues J-J, Goldberg M (2000) In vivo study of the pulp reaction to Fuji IX, a glass ionomer cement. J Dent 28:413– 422
- 73. Soheili Majd E, Goldberg M, Stanislawski L (2003) In vitre effects of ascorbate and Trolox on the biocompatibility of dental restorative materials. Biomaterials 24:3–9
- 74. Spahl W, Budzikiewicz H, Geursten W (1998) Determination of leachable components from four commercial dental composites by gas and liquid chromatography/mass spectrometry. J Dent 26:137–145
- Stanislawski L, Daniau X, Lauti A, Goldberg M (1999) Factors responsible for pulp cell cytotoxicity induced by resin-modified glass ionomer cements. J Biomed Mater Res 48:277–288
- 76. Stanislawski L, Soheili-Majd E, Perianin A, Goldberg M (2000) Dental restorative biomaterials induce glutathione depletion in cultured human gingival fibroblast: protective effect of *N*-acetyl cysteine. J Biomed Mater Res 51:469–474
- 77. Stanislawski L, Lefeuvre M, Bourd K, Soheili-Majd E, Goldberg M, Perianin A (2003) TEGDMA-induced toxicity in human fibroblasts is associated with early and drastic glutathione depletion with subsequent production of oxygen reactive species. J Biomed Mater Res 66:476–482
- Szep S, Kumkel A, Ronge K, Heidemann D (2002) Cytotoxicity of modern dentin adhesives: in vitro testing on gingival fibroblasts. J Biomed Mater Res 63:53–60
- Tarumi H, Imazoto S, Narimatsu M, Matsuo M, Ebisu S (2000) Estrogenicity of fissure sealants and adhesive resins determined by reporter gene assay. J Dent Res 79:1838–1843
- Thonemann B, Schmalz G, Hiller KA, Schweikl H (2002) Responses of L929 mouse fibroblasts, primary and immortalized bovine dental papilla-derived cells lines to dental resin components. Dent Mater 18:318–323
- Vamnes JS, Lygre GB, Grönningsæter AG, Gjerdet NR (2004) Four years of clinical experience with adverse reaction unit for dental biomaterials. Community Dent Oral Epidemiol 32:150– 157
- Wallenhammar L-M, Örtengren U, Andreasson H, Barregärd L, Björkner B, Karlsson S, Wrangssjö K, Meding B (2000) Contact allergy and hand eczema in Swedish dentists. Contact Dermatitis 43:192–199

Copyright of Clinical Oral Investigations is the property of Springer Science & Business Media B.V. and its content may not be copied or emailed to multiple sites or posted to a listserv without the copyright holder's express written permission. However, users may print, download, or email articles for individual use.