In vitro cytotoxicity of orthodontic archwires in cortical cell

cultures

Alexis David and Doug Lobner

Department of Biomedical Sciences and School of Dentistry, Marquette University, Milwaukee, USA

SUMMARY There have been a number of studies regarding the toxicity of orthodontic archwires, but little is known concerning the mechanism of their toxicity. This investigation used murine cortical cell cultures to examine the *in vitro* neurotoxicity of commonly used orthodontic metallic archwire alloys. The materials examined included 0.016 inch nickel-titanium (NiTi), copper-nickel-titanium, titanium-molybdenum, Elgiloy, and stainless steel archwire alloys. Standard sized samples of each material were placed on tissue culture inserts suspended above the cell cultures. Neuronal death was determined using the lactate dehydrogenase release assay 24 hours after exposure to the archwires.

The results indicated that NiTi, copper-nickel-titanium and titanium-molybdenum alloys were not neurotoxic, while stainless steel and Elgiloy were significantly toxic. Washing the archwires for 7 days in a saline solution did not alter the toxicity. However, the free radical scavenger, trolox, blocked the toxicity of both stainless steel and Elgiloy, indicating that the death was free radical mediated. The caspase inhibitor, Z-VAI-Ala-Asp-fluoromethylketone (zVAD-FMK), blocked the toxicity of stainless steel, but not Elgiloy, suggesting that stainless steel induced apoptosis. Further evidence that stainless steel induced apoptosis was provided by propidium staining which showed nuclear chromatin condensation and fragmentation into discrete spherical or irregular shapes, characteristic of apoptosis. The specific metal responsible for the toxicity was not determined; the metals common to each of the toxic archwires were nickel, iron, and chromium.

Introduction

A number of characteristics have been used to describe the properties of an ideal orthodontic archwire. The wire should have a large springback, low stiffness, good formability, high stored energy, biocompatibility, environmental stability, low surface friction, and the capability to be welded or soldered to auxiliaries (Kapila and Sachdeva, 1989). Currently no single orthodontic wire alloy has all of these ideal qualities and each wire is therefore selected on the basis of its strengths and limitations.

The biocompatibility of archwires is largely determined by their metal composition. The presence of nickel in some archwires has been of particular concern. Nickel allergy is the most common contact allergy in females in the USA and Europe (Staerkjaer and Menné, 1990; Bass et al., 1993). Allergic reactions to orthodontic appliances have been reported in the literature (Dunlap et al., 1989). In a study of both corrosion and cellular immune responses to nickel-containing archwires, it was found that the quantity of nickel released from wires in synthetic saliva was 700 times lower than the concentration of metal required to produce cytotoxic effects in human peripheral blood mononuclear cells from both nickel-sensitive and nickel-non-sensitive individuals (Jia et al., 1999). Nickel and chromium levels in the blood of patients prior to orthodontic treatment, and 2 and 5 months following the start of treatment, revealed that corrosion from these appliances did not increase blood levels of these two metals even in circumstances where nickel-titanium (NiTi) wires were used during treatment (Bishara *et al.*, 1993).

Metals other than nickel are present in orthodontic archwires. The potential for toxicity due to the release of each of these metals exists. The aim of this investigation was to study the *in vitro* neurotoxic effects of commonly used metallic orthodontic archwires on murine cortical cells. This study represents the first known characterization of the effects of orthodontic materials on cortical cell cultures. The most commonly used orthodontic archwire alloys, NiTi, copper-nickel-titanium, titanium-molybdenum, Elgiloy, and stainless steel, were investigated. Further experiments were conducted to characterize the mechanism of toxicity for those wires that caused significant toxicity.

Materials and methods

Materials

Timed, pregnant, Swiss Webster mice were obtained from Charles River Laboratories (Wilmington, Delaware, USA). The following were investigated: NiTi, coppernickel-titanium, titanium-molybdenum (0.016 inch diameter) archwires (Ormco/Sybron, Glendora, California, USA), stainless steel (0.016 inch diameter) archwires and Transbond[™] XT light cure adhesive (3M Unitek, Monrovia, California, USA), Blue Elgilov (0.016 inch diameter) archwires (Rocky Mountain Orthodontics, Denver, Colorado, USA), and Band-Lok[™] adhesive (Reliance Orthodontic Products Inc., Itasca, Illinois, USA). The exact composition of each archwire is given in Table 1. The archwires were cut into standard sized pieces (average weight = 2.9 ± 0.1 mg). Five pieces of each wire were then placed on tissue culture inserts suspended above the cultured cells. In this way the elastics were in contact with the media bathing the cultures, but not in direct contact with the cells. This system avoids possible cell damage due to physical disruption of the cells. Serum was obtained from Life Technologies (Gaithersburg, Maryland, USA) and Z-VAl-Ala-Asp-fluoromethylketone (zVAD-FMK) from Research Biochemicals International (Natick, Massachusetts, USA). All other chemicals were obtained from Sigma (St. Louis, Missouri, USA).

Cortical cultures

Mixed cerebral cortical cell cultures containing both neuronal and glial cells were prepared from foetal (15–16 day gestation) mice as previously described (Asrari and Lobner, 2001). Dissociated cortical cells were plated on 24-well plates coated with poly-D-lysine and laminin in Eagles' Minimal Essential Medium (MEM, Earle's salts,

Table 1	Composition	of the tested	orthodontic	archwires*.
---------	-------------	---------------	-------------	-------------

Category of material	Composition (%)	
NiTi	54 nickel 46 titanium	
CuNiTi	49.10 nickel 45.64 titanium 5.00 copper 0.20 chromium 0.06 carbon	
ТМА	~ 80–85 titanium 10–13 molybdenum 3.75–5.25 tin 0.10 carbon	
Elgiloy®	39 cobalt 21 chromium 16 iron 14 nickel 8 molybdenum	
Stainless steel (Unitek)	72 iron 18 chromium 8 nickel 1 manganese	

*According to the most current company material safety data sheets.

NiTi, nickel-titanium; CuNiTi, copper-nickel-titanium; TMA, titanium-molybdenum alloy.

supplied glutamine-free) supplemented with 5 per cent heat-inactivated horse serum, 5 per cent foetal bovine serum, 2 mM glutamine and glucose (total 21 mM). Cultures were maintained in humidified 5 per cent CO_2 incubators at 37°C. The mice were handled in accordance with a protocol approved by the institutional animal care committee.

Lactate dehydrogenase (LDH) release assay

Cell death was quantitatively assessed by the measurement of LDH, released from damaged or destroyed cells, in the extracellular fluid 24 hours after the insult was started. Blank LDH levels were subtracted from insult LDH values, and the results normalized to 100 per cent neuronal death caused by addition of the glutamate receptor agonist, 500 μ M N-methyl-D-aspartate (NMDA). Control experiments have previously shown that the efflux of LDH occurring from either necrotic or apoptotic cells is proportional to the number of neurons damaged or destroyed (Koh and Choi, 1987; Gwag *et al.*, 1995).

Propidium iodide staining

The cultures were exposed to the non-vital dye propidium iodide (10 μ M) for 30 minutes, following 24 hours of exposure to the archwires. Digital images were taken with a Diagnostic Instruments spot camera at a magnification of ×400 and presented as black and white images.

Statistical analysis

Statistical calculations were performed using one-way ANOVA followed by Dunnett's *post hoc* test. P < 0.05 was considered to indicate significant differences.

Results

The *in vitro* neurotoxicity of orthodontic metallic archwires was determined using cortical cell cultures. The alloys tested included NiTi, copper-nickel-titanium, titanium-molybdenum, Elgiloy, and stainless steel. After a 24 hour exposure, only Elgiloy and stainless steel caused significant neurotoxicity (Figure 1). The cultures used for these experiments contained both neuronal and glial cells. However, Elgiloy and stainless steel appeared to cause the death of only neurons, as similar exposure of the alloys to pure glial cultures did not cause any toxicity (data not shown).

Experiments were conducted to characterize the effects of washing the toxic alloy samples and to determine the mechanism of their toxicity. Washing the Elgiloy and stainless steel samples with Eagles' MEM for 7 days did not significantly affect the toxicity compared with unwashed samples (Figure 2). The effects of a free radical scavenger, trolox, an NMDA-type



Figure 1 Toxicity of archwires in cortical cell cultures. The bars show percentage cell death (mean \pm standard error of the mean, n = 8–16). Cell death was quantified by measuring the release of lactate dehydrogenase (LDH) 24 hours after the beginning of the insult. Sham wash values were subtracted, and the results were scaled to the level measured in sister cultures exposed to 500 μ M N-methyl-D-aspartate (NMDA) for 24 hours (= 100, this exposure induced near-complete neuronal death). *Significant toxicity. NiTi, nickel-titanium; CuNiTi, copper-nickel-titanium; TMA, titaniummolybdenum alloy; El, Elgiloy; SS, stainless steel.

glutamate receptor antagonist, MK-801, and a caspase inhibitor, zVAD-FMK, were also tested on the toxicity induced by Elgiloy and stainless steel (Figure 2). Trolox significantly attenuated the neurotoxicity induced by Elgiloy and stainless steel. MK-801 did not attenuate, and in fact potentiated, the toxicity of both Elgiloy and stainless steel. zVAD-FMK was protective against stainless steel toxicity, but not Elgiloy toxicity. This last result suggests that stainless steel induced apoptosis, while Elgiloy induced necrosis.

The type of death induced was further investigated using propidium iodide staining. In control cultures there was very little propidium iodide staining (Figure 3a), indicating that most cells were alive. Exposure to the protein kinase inhibitor, staurosporine, which is known to induce apoptosis in this culture system (Koh et al., 1995), caused nuclear chromatin condensation and fragmentation into discrete spherical or irregular shapes characteristic of apoptosis (Figure 3b). Exposure to NMDA, which is known to induce necrosis in this culture system (Gwag et al., 1997), caused diffuse nuclear staining indicating generalized, random, DNA breakdown, characteristic of necrosis (Figure 3c). Exposure to Elgiloy (Figure 3d) caused nuclear staining similar to NMDA, while stainless steel (Figure 3e) resulted in staining similar to that caused by staurosporine. The propidium iodide staining induced by stainless steel was largely eliminated by the addition of zVAD-FMK (Figure 3f).

Discussion

Previous studies of the *in vitro* toxicity of archwires have been carried out using fibroblasts (Ryhänen *et al.*, 1997;



Figure 2 The effects of washing and potential protective agents on Elgiloy (A) and stainless steel (B) toxicity. The bars show percentage cell death (mean \pm standard error of the mean, n = 8-16). *Significant difference from control toxicity (alloy without any drug). Wash, alloys washed in culture media for 7 days; Trol, 100 µM trolox (free radical scavenger); MK, 10 µM MK-801 [N-methyl-D-aspartate (NMDA) receptor antagonist]; ZVAD, 100 µM Z-VAl-Ala-Asp-fluoromethylketone (zVAD-FMK; caspase inhibitor).

Wever *et al.*, 1997; Rose *et al.*, 1998; Es-Souni *et al.*, 2003), osteoblasts (Ryhänen *et al.*, 1997; Wever *et al.*, 1997), and smooth muscle cells (Shih *et al.*, 2000, 2001). The culture system used in the current investigation was a primary neuronal culture. The main difference between this system and those previously used is that neurons are highly susceptible to many insults (Mattson *et al.*, 1995). However, the results are generally consistent with previous studies in that Elgiloy and stainless steel were toxic (Rose *et al.*, 1998). Research regarding the toxicity of NiTi archwires has been variable, with indications that it is both toxic (Shih *et al.*, 2000, 2001) and non-toxic (Ryhänen *et al.*, 1997; Wever *et al.*, 1997). The present results indicated no toxicity of NiTi archwires.

The lack of protective effect provided by the NMDAtype glutamate receptor antagonist MK-801 indicates that the release of glutamate was not a factor in the toxicity of the archwires. The potentiation of the injury by MK-801 was somewhat surprising. The addition of MK-801 attenuates a number of different insults in this culture system (Monyer *et al.*, 1989; Koh and Choi, 1994), although a blockade of glutamate receptors for



Figure 3 Propidium iodide staining following sham wash (A), 200 μ M staurosporine (B), 10 μ M N-methyl-D-aspartate (NMDA) (C), Elgiloy (D), stainless steel (E), or stainless steel plus 100 μ M Z-VAl-Ala-Asp-fluoromethylketone (zVAD-FMK) (F). Propidium iodide (10 μ M) was added for 30 minutes, 24 hours after the beginning of the insult. Bar = 50 μ m.

an extended period of time can cause toxicity (Hwang *et al.*, 1999).

It was not definitively determined what metal was responsible for the toxicity of Elgiloy and stainless steel. However, given the composition of the toxic and nontoxic archwires (Table 1), it appears likely that the toxic component was nickel, iron, or chromium. Nickel is also present at much higher levels in NiTi and copper-nickeltitanium archwires, which were not toxic. However, these archwires also contain titanium which is known to decrease the release of metals due to passive film formation (Gil et al., 1999). The fact that the toxicity was blocked by the free radical scavenger trolox also argues for nickel, iron, or chromium being the toxic component. Nickel, iron, and chromium can each enhance free radical production through a Fenton-like reaction (Torreilles et al., 1990; Halliwell and Gutteridge, 1992; Sugden et al., 1992) and each is known to be neurotoxic (Diaz-Mayans et al., 1986; Evan et al., 1995; Lobner et al., 2003).

The type of cell death, apoptosis or necrosis, caused by Elgiloy and stainless steel was determined. Apoptosis, or programmed cell death, involves a fundamental series of morphological changes (Kerr et al., 1972). Apoptosis plays an important role in the physiological turnover of normal cells and the maintenance of tissue homeostasis. Moreover, it can be observed in cells following exposure to specific toxins (Granchi et al., 2000). The other mechanism by which eukaryotic cells die is necrosis. This degenerative process occurs in response to severe hypoxia, lytic viral infections, complement attack, hyperthermia, and exposure to toxic chemicals (Kerr et al., 1972; Granchi et al., 2000). Many apoptotic pathways depend on the activation of caspases or cysteine proteases that act to cleave cytosolic and nuclear proteins, ultimately leading to apoptosis (Kidd, 1998). The caspase inhibitor, zVAD-FMK, acts to block the activation of these enzymes and is known to block apoptosis in this culture system (Lobner, 2000). Consequently, the decreased level of cell death observed for stainless steel-exposed cortical cultures in the presence of zVAD-FMK suggests death by apoptosis. Propidium iodide staining of the archwire-exposed cultures was used to identify morphological differences between apoptotic and necrotic cells (Lobner *et al.*, 2003). Cortical cultures exposed to Elgiloy exhibited diffuse nuclear staining typical of necrosis, while cultures exposed to stainless steel demonstrated chromatin condensation and fragmentation into irregular shapes, features characteristic of apoptosis. Taken together, the pharmacological results using zVAD-FMK and the morphological results obtained with propidium iodide staining, it is clear that Elgiloy induces necrosis and stainless steel induces apoptosis.

Iron causes necrosis in cortical cell cultures (Lobner et al., 2003). There are no data concerning the type of cell death caused by nickel or chromium in cortical cell cultures. However, nickel and chromium are known to induce apoptosis in other cell types (Chen et al., 2001; Kim et al., 2002). Because stainless steel induced apoptosis and Elgiloy induced necrosis, the results are most consistent with iron being responsible for Elgiloy toxicity, with nickel or chromium being responsible for stainless steel toxicity. However, measurement of the release of the metals will be required to definitely determine the metal responsible for the toxicity of the archwires. It should also be noted that no attempt was made to mimic clinical conditions which would involve the presence of factors such as ageing of the archwires and pH fluctuations of the bathing media.

It appears unlikely that the release of any metal from orthodontic archwires presents a health risk. Nickel, iron, and chromium are ubiquitous in the diet and ingestion of high levels is required to cause health problems (Anderson, 1997; Schumann, 2001). The fact that these alloys release metals at sufficiently high levels to cause neurotoxicity is not of great concern regarding archwires, but may be a consideration in situations where these alloys are used in restricted spaces where the released metals could accumulate.

Address for correspondence

Doug Lobner Department of Biomedical Sciences Marquette University 561 N. 15th Street, Rm 426 Milwaukee WI 53201 USA

Acknowledgements

This investigation was supported by NIH/NIA grant AG16708. The authors are grateful to Julie Hjelmhaug for her technical assistance.

References

- Anderson R A 1997 Chromium as an essential nutrient for humans. Regulatory Toxicology and Pharmacology 26: S35–41
- Asrari M, Lobner D 2001 Calcitonin potentiates oxygen-glucose deprivation-induced neuronal death. Experimental Neurology 167: 183–188
- Bass J K, Fine H, Cisneros G J 1993 Nickel hypersensitivity in the orthodontic patient. American Journal of Orthodontics and Dentofacial Orthopedics 103: 280–285
- Bishara S E, Barret R D, Selim M I 1993 Biodegradation of orthodontic appliances. Part II. Changes in the blood level of nickel. American Journal of Orthodontics and Dentofacial Orthopedics 103: 115–119
- Chen F, Vallyathan V, Castranova V, Shi X 2001 Cell apoptosis induced by carcinogenic metals. Molecular and Cellular Biochemistry 222: 183–188
- Diaz-Mayans J, Laborda R, Nunez A 1986 Hexavalent chromium effects on motor activity and some metabolic aspects of Wistar albino rats. Comparative Biochemistry and Physiology C 83: 191–195
- Dunlap C L, Vincent S K, Barker B F 1989 Allergic reaction to orthodontic wire: report of case. Journal of the American Dental Association 118: 449–450
- Es-Souni M, Fischer-Brandies H, Es-Souni M 2003 On the *in vitro* biocompatibility of Elgiloy, a Co-based alloy, compared to two titanium alloys. Journal of Orofacial Orthopedics 64: 16–26
- Evans J E, Miller M L, Andringa A, Hastings L 1995 Behavioral, histological, and neurochemical effects of nickel (II) on the rat olfactory system. Toxicology and Applied Pharmacology 130: 209–220
- Gil F J, Sanchez L A, Espias A, Planell J A 1999 *In vitro* corrosion behavior and metallic ion release of different prostodontic alloys. International Dental Journal 49: 361–367
- Granchi D *et al.* 2000 Modulation of pro- and anti-apoptotic genes in lymphocytes exposed to bone cements. Journal of Biomaterials Science. Polymer Edition 11: 633–646
- Gwag B J, Lobner D, Koh J Y, Wie M B, Choi D W 1995 Blockade of glutamate receptors unmasks neuronal apoptosis after oxygenglucose deprivation *in vitro*. Neuroscience 68: 615–619
- Gwag B J, Koh J Y, DeMaro J A, Ying H S, Jacquin M, Choi D W 1997 Slowly triggered excitotoxicity occurs by necrosis in cortical cultures. Neuroscience 77: 393–401
- Halliwell B, Gutteridge J M 1992 Biologically relevant metal iondependent hydroxyl radical generation. An update. FEBS Letters 307: 108–112
- Hwang J Y, Kim Y H, Ahn Y H, Wie M B, Koh J Y 1999 N-methy-D-aspartate receptor blockade induces neuronal apoptosis in cortical culture. Experimental Neurology 159: 124–130
- Jia W *et al.* 1999 Nickel release from orthodontic arch wires and cellular immune response to various nickel concentrations. Journal of Biomedical Materials Research 48: 488–495
- Kapila S, Sachdeva R 1989 Mechanical properties and clinical applications of orthodontic wires. American Journal of Orthodontics and Dentofacial Orthopedics 96: 100–109
- Kerr J F R, Wyllie A H, Currie A R 1972 Apoptosis: a basic biological phenomenon with wide-ranging implications in tissue kinetics. British Journal of Cancer 20: 273–282
- Kidd V J 1998 Proteolytic activities that mediate apoptosis. Annual Review of Physiology 60: 533–573
- Kim K, Lee S H, Seo Y R, Perkins S N, Kasprzak K S 2002 Nickel (II)-induced apoptosis in murine T cell hybridoma cells is associated with increased fas ligand expression. Toxicology and Applied Pharmacology 185: 41–47

- Koh J Y, Choi D W 1987 Quantitative determination of glutamate mediated cortical neuronal injury in cell culture by lactate dehydrogenase efflux assay. Journal of Neuroscience Methods 20: 83–90
- Koh J Y, Choi D W 1994 Zinc toxicity on cultured cortical neurons: involvement of N-methyl-D-aspartate receptors. Neuroscience 60: 1049–1057
- Koh J Y et al. 1995 Staurosporine-induced neuronal apoptosis. Experimental Neurology 135: 153–159
- Lobner D 2000 Comparison of the LDH and MTT assays for quantifying cell death: validity for neuronal apoptosis? Journal of Neuroscience Methods 96: 147–152
- Lobner D, Golner S, Hjelmhaug J 2003 Neurotrophic factor effects on oxidative stress-induced neuronal death. Neurochemical Research 28: 755–762
- Mattson M P, Barger S W, Begley J G, Mark R J 1995 Calcium, free radicals, and excitotoxic neuronal death in primary cell culture. Methods in Cell Biology 46: 187–216
- Monyer H, Goldberg M P, Choi D W 1989 Glucose deprivation neuronal injury in cortical culture. Brain Research 483: 347–354
- Rose E C, Jonas I E, Kappert H F 1998 *In vitro* investigation into the biological assessment of orthodontic wires. Journal of Orofacial Orthopedics 59: 253–264

- Ryhänen J *et al.* 1997 Biocompatibility of nickel-titanium shape memory metal and its corrosion behavior in human cell cultures. Journal of Biomedical Materials Research 41: 481–488
- Schumann K 2001 Safety aspects of iron in food. Annals of Nutrition and Metabolism 45: 91–101
- Shih C-C *et al.* 2000 The cytotoxicity of corrosion products of nitinol stent wire on cultured smooth muscle cells. Journal of Biomedical Materials Research 52: 395–403
- Shih C-C *et al.* 2001 Growth inhibition of cultured smooth muscle cells by corrosion products of 316L stainless steel wire. Journal of Biomedical Materials Research 57: 200–207
- Staerkjaer L, Menné T 1990 Nickel allergy and orthodontic treatment. European Journal of Orthodontics 12: 284–289
- Sugden K D, Geer R D, Rogers S J 1992 Oxygen radical-mediated DNA damage by redox-active Cr(III) complexes. Biochemistry 31: 11626–11631
- Torreilles J, Guerin M C, Slaoui-Hasnaoui A 1990 Nickel (II) complexes of histidyl-peptides as Fenton-reaction catalysts. Free Radical Research Communications 11: 159–166
- Wever D J, Veldhuizen A G, Sanders M M, Schakenraad J M, van Horn J R 1997 Cytotoxic, allergic and genotoxic activity of a nickel-titanium alloy. Biomaterials 18: 1115–1120

Copyright of European Journal of Orthodontics is the property of Oxford University Press / USA and its content may not be copied or emailed to multiple sites or posted to a listserv without the copyright holder's express written permission. However, users may print, download, or email articles for individual use.