Microtensile Bond Strength of Different Adhesive Systems to Primary and Permanent Dentin

Fabio Zovico Maxnuck Soares, DDS¹ Rachel de Oliveira Rocha, DDS, MS, PhD² Daniela Prócida Raggio, DDS, MS, PhD² Fernanda Tranchesi Sadek, DDS, MS. PhD² Paulo Eduardo Capel Cardoso, DDS, MS, PhD³

Abstract

Purpose: The aims of this in vitro study were to: (1) compare bond strength of different adhesive systems to primary and permanent dentin using microtensile test; and (2) evaluate the interaction of these materials to primary and permanent dentin by means of scanning electron microscopy (SEM).

Methods: Middle-coronal dentin surfaces of 18 exfoliated primary and 18 extracted permanent molars were exposed and teeth were randomly divided, according to their adhesive system, into 3 groups (N=6 per group): (1) Clearfil SE Bond (SE); (2) One Up Bond F (OU); and (3) Single Bond (SB). Then, 5-mm high composite blocks were constructed. After bonding procedures, the teeth were stored in distilled water at 37°C for 24 hours prior to the specimens' preparation. For the microtensile test, teeth (N=5 per group) were longitudinally sectioned into 2 axes rendering beam-specimens that were glued to special devices, which were mounted in a Universal Testing Machine to be loaded under a crosshead speed of 1 mm/min until fracture. One tooth of each group was prepared for SEM. **Results:** Microtensile bond strength mean values (MPa) to primary/permanent dentin were: (1) SE=60.0/61.4; (2) OU=54.5/53.3; and (3) SB=70.1/64.9. Two-way analysis of variance (ANOVA) showed no significant differences (*P*>.05) for the bond strength values among primary and permanent dentin groups, neither among groups SE×SB and SE×OU. SEM images of SE and SB showed a well-defined, uniform, and continuous hybrid layer. A continuous hybrid layer, however, was not found for OU.

Conclusions: Bond strength and micromorphologic characteristics of the adhesive systems evaluated were not influenced by the substrate. OU achieved worse results. (Pediatr Dent 2005;27:457-462)

Keywords: Dental Bonding, Dentin, Tensile Strength, Tooth, Primary

Received July 13, 2005 Revision Accepted October 5, 2005

A dhesive systems are widely used in daily clinical practice, and new products are constantly developed that improve on their predecessors¹ in the areas of: (1) technical simplification²; (2) reduced application time; and (3) minimized procedure errors.³ These simplified materials can be classified in 2 main categories:

- total-etch single bottle systems that require a previous etching procedure, generally with phosphoric acid, and that include primer and bond in only one bottle;
- 2. self-etching systems, which do not require separately etched procedures, since the etching step is combined with the acidic primer application.

In the second case, demineralization and resin monomer infiltration occur simultaneously,⁴ thereby reducing possible discrepancies and gap formation.⁵ Acidic monomers can be combined with the primer, requiring a separate bond application (self-etching primers). Acidic primer and bond can be combined in a single clinical step (self-etching adhesives or all-in-ones), thus achieving an important advantage in technique simplification.⁶⁻⁸

Despite these advantages, clinical indication depends on bonding performance. Bond strength to enamel or dentin is an important indicator of an adhesive systems' effectiveness, since the bonding layer must support not only composite shrinkage stress but also occlusal forces—mainly in restorations in stress-bearing areas—to avoid gap formation⁹ that can lead to microleakage, secondary caries, and postoperative sensitivity.¹⁰

A great number of studies have already evaluated the bond strength of simplified adhesive systems to permanent

¹Dr. Soares is a doctoral student, and ³Dr. Cardoso is professor, Department of Dental Materials; ²Drs. Rocha, Raggio, and Sadek were doctoral students at the time of the study, Department of Pediatric Dentistry, all at the University of São Paulo, São Paulo, Brazil. Correspond with Dr. Cardoso at paulocapel@uol.com.br

dentin.¹¹⁻¹⁵ Only limited information, however, is available in the literature regarding their performance on primary teeth.^{16,17} Moreover, measurement of bond strength to primary dentin is controversial, since some studies showed lower bond strength to this substrate compared to permanent dentin,18-20 while others demonstrated similar21-23 or higher values for primary dentin.16 Differences in the percentage of mineral components-in terms of tubular density, diameter, and intrinsic moisture to primary and permanent teeth-may influence adhesive system performance.^{16,24-26} Nör et al²⁷ demonstrated that primary dentin is more reactive to acid etching than permanent dentin, and they suggested different application protocols for primary teeth. Contrary results have been reported concerning hybrid layer formation,^{17,18} indicating that primary dentin is less permeable than permanent dentin.24 Moreover, a direct relationship does not appear to exist between dentin appearance after acid conditioning as verified in micromorphologic analyses and bond strength values.18 Thus, it is important to clarify the effectiveness of simplified adhesive systems to primary and permanent dentin.

Besides bond strength measurements, another important tool used to evaluate adhesive system performance is dentin/adhesive interface observation by means of scanning electron microscopy (SEM).²⁸⁻³¹ Hybrid layer and resin tag formation and the intimate contact with underlining dentin are significant occurrences that can be observed under SEM, clarifying the interaction between adhesive systems and dentin.

Therefore, the aims of this in vitro study were to: (1) compare bond strength of different adhesive systems to primary and permanent dentin using a microtensile test; and (2) evaluate the interaction of these materials to primary and permanent dentin by means of SEM. The null hypotheses tested were:

- 1. There are no differences in primary and permanent bond strength and interfacial micromorphology.
- 2. There are no differences in bond strength and interfacial micromorphology achieved by different tested adhesive systems.

Methods

This study's protocol was reviewed and approved by the local ethical committee (Comitê de Ética em Pesquisa da Faculdade de Odontologia da Universidade de São Paulo, protocol No. 190/02).

Eighteen sound exfoliated primary first and second molars and 18 sound third molars extracted for orthodontic reasons were collected, stored in 0.5% chloramine T at 4°C, and used within 3 months after retrieval. The occlusal enamel was removed with a water-cooled diamond disc in a cutting machine (Labcut 1010, Extec Co, Enfield, Conn) to obtain flat dentin surfaces. Surrounding enamel was also removed with a diamond bur in a high-speed handpiece with water spray. Exposed occlusal dentin surfaces were then polished with 600-grit silicon carbide paper under running water to create a standardized smear layer.¹⁷

Primary and permanent teeth were randomly divided, according to the adhesive system tested, into 3 groups (N=6 per group): (1) Clearfil SE Bond (SE [Kuraray Medical Inc, Osaka, Japan]); (2) One Up Bond F (OU [Tokuyama Corp, Tokyo, Japan]); and (3) Single Bond (SB [3M ESPE St. Paul, Minn]). All materials were applied on dentin surfaces according to the manufacturers' instructions. A fresh drop of each adhesive system was used for each tooth, applied in the same way to primary and permanent dentin. For SB, after rinsing the phosphoric acid, a moist dentin surface was created with a 5-second stream of oil-free air 20 cm away from the tooth. Care was taken to not desiccate the dentin with this air stream.

After bonding procedures, resin composite blocks were constructed (Z100, 3M ESPE, St. Paul, Minn) in increments of 2 mm, individually light cured for 40 seconds (Optilux 401, Demetron/Kerr, Orange, Calif; 500 nW/ cm²), until it was 6-mm high. Teeth were stored in distilled water at 37°C for 24 hours prior to preparation for the microtensile test or SEM evaluation.

Five teeth of each subgroup were randomly selected and longitudinally sectioned into 2 axes with a water-cooled disc (Extec 12205, Extec Co, Enfield, Conn) mounted in a cutting machine (Labcut 1010, Extec Co, Enfield, Conn). This was done to obtain beam-shaped specimens with a cross-sectional area of 0.4 mm² for microtensile tests. Each of the beams was glued with Super Bonder gel (Henkel Loctite, Itapevi, Brazil) to specially designed microtensile grips mounted on a universal testing machine (Kratos Dinamometros, Embu, Brazil). When the loading machine was activated under tension at a crosshead speed of 1 mm/min, purely tensile forces were applied to the microtensile beams until the specimens fractured. Fractured specimens were then examined under a stereomicroscope (x25 magnification) to analyze fracture mode, which was classified as adhesive or cohesive failure. Only specimens with adhesive failures were used to calculate bond strength means.

Microtensile bond strength data were first analyzed with a regression analysis to verify the influence of tooth of origin in the measured strengths. Since it was statistically significant, microtensile data were analyzed by tooth (N=5 per group) and not by beams using 2-way ANOVA with subsequent Tukey test at P<.05. Also, a chi-square test was performed to analyze the fracture mode proportions among the various materials and substrate.

For SEM analysis, 1 tooth in each experimental group was cut in half perpendicularly to the bonded interface with a water-cooled diamond disc. Each half was polished with 1,200- and 2,000-grit sandpaper under refrigeration. The final polish was obtained with increasingly fine diamond pastes (1 μ m and 0.25 μ m, METAD I and II, respectively, Buehler, Lake Bluff, III). Debris was ultrasonically removed (Cavitron 3000, LD Caulk, New York, NY) for 10 minutes between each polishing procedure. After obtaining specular brightness, specimens were stored at room temperature in 2.5% buffered glutaraldehyde solution (pH=7.4) and ultrasonically cleaned for 10 minutes before being exposed to a 50% phosphoric acid solution for 5 seconds and to a 1% sodium hypochlorite for 10 minutes. This technique demineralized any dentin that was not infiltrated with resin so that the dentin could be dehydrated with silica for 24 hours.^{32,33} Specimens were gold sputtered and observed under a Philips XL30 scanning electron microscope (Philips, Eindhoven, The Netherlands).

Results

Microtensile bond strength mean values for the adhesive systems tested are summarized in Table 1. Regarding substrate factor, primary and permanent dentin showed similar bond strength values, with no significant differences (P>.05). On the other hand, materials were statistically different (P<.05). SB showed bond strength values significantly higher that OU, whereas SE showed intermediate bond strength values similar to the other 2 systems (P>.05).

Table 2 shows failure mode results. A chi-square test confirmed that there were no statistically significant differences in fracture mode proportion for primary and permanent dentin or among the various materials. Even though it was not statistically significant, SB showed a higher number of cohesive fractures regardless of the substrate.

SEM images of SE and SB showed good adaptation and established formation of a uniform hybrid layer to primary dentin as well as to permanent dentin. For SB, the hybrid layer was about 2-µm thick (Figure 1), which is almost

Table 1. Bond Strength Mean Values (MPa)and Standard Deviation for the Adhesive SystemsTested, Both on Primary and Permanent Dentin

Adhesive systems	Means±SD*		
	Primary dentin	Permanent dentin	
Clearfil SE Bond	60.0±8.9 ^{a,b}	61.4±6.4 ^{a,b}	
One Up Bond F	54.5±2.4 ^b	53.3±3.7 ^b	
Single Bond	70.1±3.8ª 64.9±10.0 ^a		

*Means with the same letters are not significantly different (P>.05).

Table 2. Fracture Mode for Experimental Groups: Chi-square Results of the Fracture Mode Proportions Among Various Materials

Adhesive systems	Adhesive/cohesive failures*			
	Primary dentin	Chi-square	Permanent dentin	Chi-square
SE	57/3	4.06 (NS)	88/2	0.78 (NS)
OU	47/2		54/2	
SB	53/8	•	82/4	*

*NS=not significant.

twice as thick as those observed for SE (Figure 2). OU SEM images (Figure 3), however, showed an even thinner hybrid layer of approximately $0.5\mu m$. Moreover, nonprotected or noninfiltrated collagen fibrils were seen (Figures 3c and 3d), which were not observed for the other materials.

Discussion

Since the development of early adhesive systems, an effort has been made to improve bond quality to dental substrate-mainly to dentin, which is more complex and less predictable than enamel.6 Despite the great number of studies that used permanent teeth, there are only a few studies that evaluated bond strength to primary dentin. Even fewer studies utilized the microtensile test, 17,34 which is now considered the most reliable adhesion testing technique that is capable of assessing the "true' interfacial strength between an adhesive and the bonding substrate, since pure tensile load is applied to reduced sections with a uniform stress distribution.35,36 As already demonstrated, in the microtensile test the specimen's bonded area is inversely proportional to bond strength values recorded.^{11,14,37} The high bond strength values obtained in this study are related to the small bonded area and to the specimen configuration used. A cross-sectioned area of approximately 0.4 mm² was employed to accommodate the reduced dimensions of primary teeth and to obtain a higher number of specimens per teeth, thereby reducing the intertooth variation.

The results found in the literature regarding bond strength to primary and permanent teeth show wide variation.^{19,20,23,38} The present study showed that the adhesive systems evaluated performed equally well on primary and permanent dentin, since neither bond strength values nor SEM micrographs showed significant differences. Similar results were already found in previous studies,²¹⁻²³ despite the fact that they employed tensile and shear bond strength tests and that morphological and structural differences existed between the substrates.

In addition, the primary teeth employed had undergone exfoliation. Hence, the dentin characteristics are expected to be different from those of younger impacted permanent teeth, which are generally used in this kind of study. However, the influence of the type of tooth on bond quality seems to be insignificant.³⁹ In the same way, SEM analysis revealed simi-

lar performances for primary and permanent dentin, emphasizing that the kind of dentition does not influence the results.

With their simplified technique, self-etching adhesives are particularly valuable in pediatric dentistry, particularly when it comes to saving time. Regardless of their easier application, however, self-etching adhesives must also be efficient. The results



Figure 1. Scanning electron microscope image of Single Bond specimens showing a uniform hybrid layer and resin tags on (a) primary dentin and on (b) permanent dentin. At a higher magnification (×20,000), details of the hybrid layer on (c) primary dentin and on (d) permanent dentin.



Figure 3. Scanning electron microscope image of One Up Bond F specimens demonstrating a thin hybrid layer and poor resins tags infiltration (a) and also a discontinuity area on primary dentin and on (b) permanent dentin. At a higher magnification (×20,000), details of the nonuniform hybrid layer and exposed collagen fibrils not infiltrated by monomers (*) on (c) primary dentin and on (d) permanent dentin.

found in the present study corroborate those from literature,^{1,13,21,35,40} confirming that 2-step self-etch systems are comparable to conventional total-etching systems in terms of bond strength and morphological characteristics. In fact, primary and permanent dentin bond strength values and morphologic characteristics observed with Clearfil SE Bond were similar to those obtained with Single Bond (*P*>.05; Figures 1 and 2). These results are also supported, regardless of the testing technique, by those obtained from Senawongse et al,¹⁸ who evaluated the performance of these materials in primary teeth by means of a microshear test.

Previous studies^{26,27} based on morphological analyses have suggested different application protocols for primary and permanent teeth based on the more intense action of conditioners in primary dentin. Nevertheless, in the present study, adhesive system applications were identical for the 2 substrates. As previously demonstrated,⁴¹ this choice was based on the concept that there was not a relationship between bond strength and hybrid layer thickness. A hybrid



Figure 2. Scanning electron microscope image of Clearfil SE Bond specimens showing a uniform hybrid layer and resin tags on (a) primary dentin and on (b) permanent dentin. At a higher magnification (×20,000), details of the hybrid layer on (c) primary dentin and on (d) permanent dentin.

layer with identical thickness was observed in both primary and permanent dentin, which agreed with previous studies^{17,19} despite differences in mineral concentration between these 2 substrates.⁴² These results confirm, once again, that hybrid layer thickness does not influence bond strength values. More relevant than hybrid layer thickness is its favorable and uniform interaction with the adjacent tooth substrate.

The 1-step self-etching system (One Up Bond F) showed the lowest bond strength among the 2 substrates compared to the total-etch system. The simultaneous etching, primer, and bond application can limit the permeation of the monomers through the substrate during demineralization. This promotes poor infiltration, which can result in areas without dentin hybridization.^{6,43} In Figure 3, a very thin and nonuniform hybrid layer can be observed, which becomes more obvious when compared to that formed by Single Bond (Figure 1). Moreover, it is possible to notice discontinuous areas in certain regions, characteristic of adhesion failure, which possibly explains the low bond strength values for this adhesive system.

During SEM specimens' preparation, samples were demineralized for 5 seconds with phosphoric acid, exposing the bottom portion of the hybrid layer and improving its visualization. For One Up Bond F, in higher magnifications (areas marked with * in Figures 3c and 3d), a collagen network is visible at the base of the hybrid layer. This is characteristic of poor monomer infiltration instead of the smooth hybrid layer surface observed for the other systems (Figures 1 and 2). This morphology pattern was observed both in primary and permanent dentin.

The methodological limitations of this in vitro study do not permit a direct extrapolation to the clinical situation. This study's results, however, suggest that the same protocol of adhesive system application can be employed with primary and permanent teeth. The micromorphologic characteristics of the hybrid layer formed with One Up Bond F suggest careful clinical use until further research corroborates its effectiveness.

Conclusions

Within the limitations of this in vitro study, the following conclusions could be made:

- 1. The adhesive systems evaluated performed similarly on primary and permanent dentin, considering their bond strength and scanning electron miscroscopy evaluation.
- 2. Well-defined hybrid layers were observed for Single Bond and Clearfil SE Bond with different thickness. These adhesive systems also produced similar bond strengths.
- 3. One Up Bond F produced a very thin and nonuniform hybrid layer showing noncontinuous regions. Bond strength values for this system were similar to Clearfil SE Bond and lower than Single Bond.

Acknowledgements

The authors are grateful to Núcleo de Apoio à Pesquisa em Materiais Dentários (NAPEM-FOUSP).

References

- 1. Tanumiharja M, Burrow MF, Tyas MJ. Microtensile bond strengths of seven dentin adhesive systems. Dent Mater 2000;16:180-187.
- Lopes GC, Baratieri LN, de Andrada MA, Vieira LC. Dental adhesion: Present state of the art and future perspectives. Quintessence Int 2002;33:213-224.
- Cardoso PE, Carrilho MR, Francci CE, Perdigao J. Microtensile bond strengths of one-bottle dentin adhesives. Am J Dent 2001;14:22-24.
- Van Meerbeek B, Perdigao J, Lambrechts P, Vanherle G. The clinical performance of adhesives. J Dent 1998;26:1-20.
- Gordan VV, Vargas MA, Cobb DS, Denehy GE. Evaluation of adhesive systems using acidic primers. Am J Dent 1997;10:219-223.
- Frankenberger R, Perdigao J, Rosa BT, Lopes M. "No-bottle" vs "multi-bottle" dentin adhesives: A microtensile bond strength and morphological study. Dent Mater 2001;17:373-380.
- Chigira H, Yukitani W, Hasegawa T, et al. Self-etching dentin primers containing phenyl-P. J Dent Res 1994;73:1088-1095.
- Watanabe I, Nakabayashi N, Pashley DH. Bonding to ground dentin by a phenyl-P self-etching primer. J Dent Res 1994;73:1212-1220.
- 9. Van Meerbeek B, Vargas M, Inoue S, et al. Adhesives and cements to promote preservation dentistry. Oper Dent 2001;6:119-144.
- Eick JD, Gwinnett AJ, Pashley DH, Robinson SJ. Current concepts on adhesion to dentin. Crit Rev Oral Biol Med 1997;8:306-335.
- 11. Sano H, Shono T, Sonoda H, et al. Relationship between surface area for adhesion and tensile bond strength: Evaluation of a micro-tensile bond test. Dent Mater 1994;10:236-240.

- 12. Pashley DH, Sano H, Ciucchi B, Yoshiyama M, Carvalho RM. Adhesion testing of dentin bonding agents: A review. Dent Mater 1995;11:117-125.
- 13. Schreiner RF, Chappell RP, Glaros AG, Eick JD. Microtensile testing of dentin adhesives. Dent Mater 1998;14:194-201.
- Phrukkanon S, Burrow MF, Tyas MJ. The effect of dentine location and tubule orientation on the bond strengths between resin and dentine. J Dent 1999;27: 265-274.
- 15. Koibuchi H, Yasuda N, Nakabayashi N. Bonding to dentin with a self-etching primer: The effect of smear layers. Dent Mater 2001;17:122-126.
- Hosoya Y, Nishiguchi M, Kashiwabara Y, Horiuchi A, Goto G. Comparison of two dentin adhesives to primary vs permanent bovine dentin. J Clin Pediatr Dent 1997;22:69-76.
- 17. Burrow MF, Nopnakeepong U, Phrukkanon S. A comparison of microtensile bond strengths of several dentin bonding systems to primary and permanent dentin. Dent Mater 2002;18:239-245.
- Senawongse P, Harnirattisai C, Shimada Y, Tagami J. Effective bond strength of current adhesive systems on deciduous and permanent dentin. Oper Dent 2004;29:196-202.
- 19. el Kalla IH, García-Godoy F. Bond strength and interfacial micromorphology of four adhesive systems in primary and permanent molars. J Dent Child 1998;65:169-176.
- 20. Salama FS, Tao L. Comparison of Gluma bond strength to primary vs permanent teeth. Pediatr Dent 1991;13:163-166.
- 21. Agostini FG, Kaaden C, Powers JM. Bond strength of self-etching primers to enamel and dentin of primary teeth. Pediatr Dent 2001;23:481-486.
- 22. Baghdadi ZD. In vitro bonding efficacy of three restorative materials to primary dentin using a one-bottle adhesive system. Gen Dent 2001;49:624-631, 632-623 (quiz).
- Fagan TR, Crall JJ, Jensen ME, Chalkley Y, Clarkson B. A comparison of two dentin bonding agents in primary and permanent teeth. Pediatr Dent 1986;8: 144-146.
- 24. Koutsi V, Noonan RG, Horner JA, Simpson MD, Matthews WG, Pashley DH. The effect of dentin depth on the permeability and ultrastructure of primary molars. Pediatr Dent 1994;16:29-35.
- 25. de Araujo FB, García-Godoy F, Issao M. A comparison of three resin bonding agents to primary tooth dentin. Pediatr Dent 1997;19:253-257.
- 26. Nor JE, Feigal RJ, Dennison JB, Edwards CA. Dentin bonding: SEM comparison of the resin-dentin interface in primary and permanent teeth. J Dent Res 1996;75:1396-1403.

- 27. Nor JE, Feigal RJ, Dennison JB, Edwards CA. Dentin bonding: SEM comparison of the dentin surface in primary and permanent teeth. Pediatr Dent 1997;19:246-252.
- 28. Sakoolnamarka R, Burrow MF, Tyas MJ. Micromorphological study of resin-dentin interface of noncarious cervical lesions. Oper Dent 2002;27:493-499.
- 29. Sano H, Yoshiyama M, Ebisu S, et al. Comparative SEM and TEM observations of nanoleakage within the hybrid layer. Oper Dent 1995;20:160-167.
- Hashimoto M, Ohno H, Kaga M, Endo K, Sano H, Oguchi H. Resin-tooth adhesive interfaces after longterm function. Am J Dent 2001;14:211-215.
- Miyazaki M, Sato M, Onose H, Moore BK. Influence of thermal cycling on dentin bond strength of twostep bonding systems. Am J Dent 1998;11:118-122.
- 32. Hashimoto M, Ohno H, Sano H, Kaga M, Oguchi H. In vitro degradation of resin-dentin bonds analyzed by microtensile bond test, scanning and transmission electron microscopy. Biomaterials 2003;24:3795-3803.
- Nikaido T, Cho E, Nakajima M, et al. Tensile bond strengths of resin cements to bovine dentin using resin coating. Am J Dent 2003;16(special issue):41A-46A.
- Cehreli ZC, Akca T, Altay N. Bond strengths of polyacid-modified resin composites and a resin-modified glass-ionomer cement to primary dentin. Am J Dent 2003;16(special issue):47A-50A.
- 35. Cardoso PE, Sadek FT, Goracci C, Ferrari M. Adhesion testing with the microtensile method: Effects of dental substrate and adhesive system on bond strength measurements. J Adhes Dent 2002;4:291-297.

- Pashley DH, Carvalho RM, Sano H, et al. The microtensile bond test: A review. J Adhes Dent 1999;1: 299-309.
- 37. Goracci C, Sadek FT, Monticelli F, Cardoso PE, Ferrari M. Influence of substrate, shape, and thickness on microtensile specimens' structural integrity and their measured bond strengths. Dent Mater 2004;20:643-654.
- 38. Jumlongras D, White GE. Bond strengths of composite resin and compomers in primary and permanent teeth. J Clin Pediatr Dent 1997;21:223-229.
- Giannini M, Chaves P, Oliveira MT. Effect of tooth age on bond strength to dentin. J Appl Oral Sci 2003; 11:342-347.
- 40. Armstrong SR, Vargas MA, Fang Q, Laffoon JE. Microtensile bond strength of a total-etch 3-step, total-etch 2-step, self-etch 2-step, and a self-etch 1-step dentin bonding system through 15-month water storage. J Adhes Dent 2003;5:47-56.
- 41. Yoshiyama M, Carvalho RM, Sano H, Horner JA, Brewer PD, Pashley DH. Regional bond strengths of resins to human root dentine. J Dent 1996;24:435-442.
- 42. Sonju Clasen AB, Ruyter IE. Quantitative determination of type A and type B carbonate in human deciduous and permanent enamel by means of Fourier transform infrared spectrometry. Adv Dent Res 1997;11:523-527.
- 43. Bouillaguet S, Gysi P, Wataha JC, et al. Bond strength of composite to dentin using conventional, one-step, and self-etching adhesive systems. J Dent 2001;29:55-61.

Abstract of the Scientific Literature

FINGERNAILS AND TOENAILS AS BIOMARKERS OF SUBCHRONIC EXPOSURE TO FLUORIDE

The aim of this article was to evaluate the use of fingernails and toenails as biomarkers of subchronic fluoride exposure from fluoride dentifrices in 2- to 3-year-old children. Ten children living in a fluoridated community were instructed to brush their teeth with: (1) a placebo dentifrice for 28 days; (2) a fluoride dentifrice (1,570 ppm) for another 28 days; and (3) a placebo dentifrice for the last 28 days. Fingernails and toenails were clipped at the beginning of the experiment and every 2 weeks for 34 weeks and analyzed for fluoride content with an electrode following hexamethyldisiloxane-facilitated diffusion. Nail fluoride concentrations ranged from 1.26 to 17.42 μ g/g, with 2 peaks seen 4 and 16 weeks after starting the use of fluoride dentifrice. A significant positive correlation was found between the fluoride concentration of fingernails and toenails. In conclusion, this study demonstrates that nails can be used as biomarkers of subchronic exposure to fluoride from dentifrices in small children.

Comments: It is important to objectively determine the levels of exposure to fluoride. Fingernails and toenails can be good alternatives to use as biomarkers to determine subchronic fluoride exposure. **JLC**

Address correspondence to Marília Afonso Rabelo Buzalaf, Octávio Pinheiro Brisolla, 9-75, Bauru SP 17012-901, Brazil.

Correa Rodrigues MH, de Magalhaes Bastos JR, Rabelo Buzaraf MA. Fingernails and toenails as biomarkers of subchronic exposure to fluoride from dentifrice in 2- to 3-year-old children. Caries Res 2004;38:109-114.

23 references

Copyright of Pediatric Dentistry is the property of American Society of Dentistry for Children and its content may not be copied or emailed to multiple sites or posted to a listserv without the copyright holder's express written permission. However, users may print, download, or email articles for individual use.