Scientific Article

Clinical Outcomes for Primary Anterior Teeth Treated with Preveneered Stainless Steel Crowns

Jeanette K. MacLean, DDS¹ • Cariann E. Champagne, DDS² • William F. Waggoner, DDS, MS³ • Marcia M. Ditmyer, PhD, CHES⁴ • Paul Casamassimo, DDS, MS⁵

Abstract: Purpose: The purpose of this retrospective study was to explore clinical outcomes for NuSmile anterior preveneered stainless steel crowns. Methods: A convenience sample of healthy children treated with anterior crowns was selected from a teaching clinic and private office. Crowns were placed by either a private practice dentist or pediatric dental resident. Clearly defined clinical outcomes were assessed by 3 calibrated examiners at recall, including: (1) presence; (2) chipping; (3) wear; (4) crazing; and (5) marginal location by clinical and radiographic examination. Factors affecting placement—such as operator experience and behavior—were also assessed. **Results:** In 46 subjects (21 females, 25 males; mean age at placement=4 years, 2 months), 226 crowns with a mean post-placement time of 12.9 months were evaluated. Only 2 crowns matched natural teeth, with NuSmile crowns lighter in 83% of subjects. Most crowns (86%) were normal in size. Eighty-eight percent resisted fracture for 6 months. All but 3 crowns resisted color change for 6 months. Canine crowns were the least successful, but overall 91% of crowns retained good to excellent clinical appearance. **Conclusions:** NuSmile anterior preveneered crowns are a clinically successful restoration for primary incisors with early childhood caries. (Pediatr Dent 2007;29:377-81) Received September 21, 2006 / Revision Accepted January 9, 2007.

KEYWORDS: ANTERIOR PRIMARY TEETH, STAINLESS STEEL CROWNS, ESTHETICS

Restoring primary incisors damaged by early childhood caries (ECC) is one of the most challenging tasks for the pediatric dentist. The gingival tissue of ECC patients tends to be inflamed, leading to hemorrhage and compromising composite esthetic restoration. Primary incisor anatomy, including small overall size, thinness of enamel and surface proximity to the relatively large dental pulp, make intracoronal restoration difficult.¹ Hence, full-coverage restorations or crowns are typically placed. Behavior management further complicates treatment.

For decades, stainless steel crowns (SSCs) have been the easiest placed and most durable restoration for severely decayed primary incisors, outperforming amalgam and composite.^{2,3} Unfortunately, they offer poor esthetics and some parents report they would rather have incisors extracted if SSCs are the only restorative option.¹ Because crowns play a crucial role in restoring a child's carious anterior teeth, es-

Correspond with Dr. Casamassimo at casamassimo.1@osu.edu

thetic alternatives to SSCs have been developed. These include: (1) open-faced crowns; (2) bonded strip crowns; and (3) preveneered SSCs.⁴⁻⁷

Open-faced crowns combine durability and esthetics, but are time consuming to complete.⁸ Hemorrhage of gingival tissue remains an issue, and metal margins around the composite facing create an often unacceptable appearance. The bonded strip crown is the most esthetic, natural-looking, complete-coverage restoration available for primary incisors,^{2.7} but is time consuming and extremely technique sensitive. Even when placed under ideal conditions, strength and resistance to wear are far from that of the SSC. A 2002 study of children whose dental treatment was accomplished under general anesthesia found that strip crowns had a failure rate of 51%, compared to a low (8%) failure rate for SSCs.³

Preveneered or resin-veneered SSCs (PVSSCs) resolve some problems associated with SSCs, open-faced crowns, and strip crowns1 and serve as a solution to restore severely carious primary incisors.² They can be placed in a single, short appointment, and their esthetics are not affected by saliva or hemorrhage.⁸⁻¹⁰ Clinical disadvantages include:

- relatively inflexible, brittle, resin facing material that tends to break when subjected to heavy force⁸;
- no crimping of the lingual surface or forcing crowns on to the teeth;

¹Dr. MacLean is a pediatric dentist in private practice in Glendale, Ariz; ²Dr. Champagne is a pediatric dentist in private practice in Reno, Nev; ³Dr. Waggoner is a pediatric dentist in private practice in Las Vegas, Nev: ⁴Dr. Ditmyer is assistant professor-in-resident, School of Dental Medicine, University of Nevada, Las Vegas, Nev; and ⁵Dr. Casamassimo is professor and head, Pediatric Dentistry Section, The Ohio State University, Columbus, Ohio.

- significant removal of tooth structure in preparation of allowing a more passive fit;
- 4. expense;
- 5. limited shade choice; and
- 6. difficulty placing multiple approximating crowns in patients with crowding or space loss due to bulk.¹

Over time, some preveneered crown facings may fracture.^{2,8,10} Heat sterilization has unknown effects on the resin facing. The various types of PVSSCs available commercially differ in terms of the: (1) method of facing attachment to the SSC; (2) shades available; (3) crown length; and (4) clinician's ability to crimp the crown.⁷

Despite their disadvantages, PVSSCs remain very popular, but very little clinical research compares the products available.¹⁰ Three clinical studies report outcomes for esthetic anterior crowns. Roberts et al evaluated clinical success and parental acceptance in 12 children with 38 preveneered crowns.¹⁰ In 2003, Kupietzky et al evaluated clinical and radiographic success in 40 children with 120 strip crowns.¹¹ In a 2004 study by Shah et al, clinical success and parental satisfaction with Kinder Krown preveneered anterior crowns were evaluated in only 12 patients with 48 crowns.¹²

This institutionally approved, retrospective study's purpose was to determine the clinical outcomes for a sample of NuSmile preveneered SSCs used to treat anterior teeth with early childhood caries.

Methods

Sample selection. Children were patients of either a private pediatric dental practice or public health clinic and had crowns placed by first- or second-year pediatric dental residents or a dentist in private practice. In total, crowns were placed by any of 10 clinicians. Subjects had 1 or more NuSmile crowns (Orthodontic Technologies, Houston, Tex), used as the PVSSC of choice in both settings. These were placed on maxillary and/or mandibular primary anterior teeth at least 6 months prior to evaluation and cemented with glass ionomer cement. Excluded were children with: (1) special needs; (2) traumatized teeth; (3) crowns placed by other than the study operators; and (4) teeth near normal exfoliation.

Procedures. Subjects in this convenience sample were approached by telephone or at their scheduled 6-month preventive care appointment and invited to participate. Following consent, an examination was done using a mouth mirror and an overhead dental light, after a supracoronal polishing with rubber cup and prophylaxis paste. Each child's oral hygiene (plaque index) was assessed by 1 of 3 calibrated examiners and recorded by a trained dental assistant prior to cleaning. A periapical radiograph of the crown(s) was made, and a standardized anterior segment digital intraoral photographic image was made of the crown(s)—displaying a

minimum of 4 maxillary anterior teeth, as well as canines, if crowned. Three nonblinded, calibrated examiners (JKM, CEC, and WFW) evaluated the crowns, and data were recorded by a trained dental assistant. The parent or guardian completed a written survey in English or Spanish to assess parental satisfaction, administered by a trained dental assistant without the presence of the examiner.

Criteria. Criteria selected for this study reflect those used in other studies and considered important in clinical acceptance of preveneered crowns. Historical and clinical variables and the scoring technique used are shown in the Figure. Calibration sessions were held prior to data collection to improve intra- and inter-rater examiner reliability, including: (1) measurement using specified instruments; (2) use of intraoral photography; and (3) identification of variables (crazing, chipping, margins, etc).

Analysis. Data were entered into an Excel spreadsheet (Microsoft Corp, Redmond, Wash) and imported into SPSS 12.0 software (SPSS, Inc, Chicago, Ill) for statistical analysis. Descriptive statistics were used to describe the demographic information. Percent response frequencies were subsequently computed. A *P*-value of .05 or better was considered significant.

Results

Patient characteristics. A total of 226 NuSmile crowns were evaluated in 46 of 49 eligible patients—21 females (46%) and 25 males (54%)—with 3 patients eliminated due to inability to obtain consent or identify the provider. Mean age at the time of crown placement was 4 years, 2 months (range=2 years, 2 months to 7 years, 9 months), and age at evaluation was 5 years, 4 months (range=2 years, 10 months to 8 years, 4 months). Mean time between placement and evaluation was 12.9 months (range=6-45 months).

Each patient had an average of 5 crowns (range=1 to12). Twenty patients were treated by first-year pediatric dental residents (43%), 22 by second-year pediatric dental residents (48%), and 4 by a private practice pediatric dentist (9%). One patient was managed with nonpharmacologic behavior management techniques alone (2%), 2 patients with nitrous oxide (4%), 1 with oral conscious sedation (2%), and 42 under general anesthesia (91%). Forty-four patients had positive behavior (96%), and 2 had negative behavior (4%). Parents reported 11 patients with a history of bruxism (24%) and 13 patients with a history of trauma to the crowned teeth (28%).

Crown functional characteristics. The functional variables are described by tooth type in the Table. When comparing the shade of the NuSmile crown to natural teeth, only 2 patient's

Figure. CRITERIA FOR ASSESSMENT OF VARIABLES RELATED TO CROWN FUNCTION.

History of bruxism	Present	Non-present				
Plaque index	No plaque	Plague on gingi one third of crow	Plaque on >50% of crown			
Provider type	Private practice DDS	First-year reside	Second-year residentt			
Behavior management	Nonpharmacologic	Nitrous oxide	Oral sedation	General Anesthesia	a	
Patient behavior	Positive: Quiet and coop	Negative: Disruptive, moving, crying				
Overall appearance	Excellent: Superior result, very natural	Good: Esthetic result, minor rotation or size discrepancies	Poor: Chipped facing, un- natural, needs improvement	Very poor: Not esthetic, detracts from appearance		
Crown type	Regular	Short		Unclear		
Retention	Present	Recemented *		Absent		
Crazing	None	<1 mm	>1<3 mm	>3 mm		
Fracture/ chipping	None	<1/3	<2/3	Complete loss		
Attrition/ wear	None		Noticeable wear			
Margin	Subgingival	At the margin		Supragingival		
Pulp therapy	None	Indirect	Pulpotomy Pulpecto		ny	
Trauma history	Traumatized		Not traumatized			
Color stability	No Change	Change	Yellow	Brown	Gray	
Shade match	Same as other teeth	Lighter		Darker		
Crown size	Natural	Bulky	ky		Too small	
Gingival margin discoloration	None		Gray			
Gingival health	Healthy	Mild inflamation	1	Inflamation with bleeding		
Radiographic pulpal health	Healthy	Changes not red treatment	quiring	Changes requiring treatment		

fractured facings were observed in 19 patients. Of the fractured crowns: (a) 24 lost less than one third of the white facing; (b) 3 lost less than two thirds of the facing; but (c) 0 had complete facing loss.

All 3 crowns with less than two thirds facing loss were maxillary laterals.

A total of 161 NuSmile crowns (71%) resisted attrition/incisal wear for at least 6 months, but 65 (29%) had noticeable wear in 28 patients. The majority of crowns, 224 (99%), resisted crazing for at least 6 months.

All but 3 crowns resisted color change for at least 6 months, with 3 canines (1 maxillary and 2 mandibular) observed to have changes in facing color (yellow) when compared to a new, unused crown.

Regarding appearance: (a) 17 patients (37%) had an excellent overall appearance; (b) 23 (50%) had a good overall appearance; (c) 4 (9%) had a poor result; and (d) \circ (0%) had very poor results.

Differences and associations between crown function and selected variables. Overall appearance was significantly associated with positive behavior (P=.005).

* Same or new crown.

(4%) shades matched. The NuSmile crown shade was lighter than the natural teeth in 38 patients (83%). This variable was not applicable in 6 patients (13%), because all adjacent teeth were either crowned or extracted. When the nonapplicable patients were eliminated, 95% of the NuSmile crown facings were lighter than the patient's natural teeth.

One hundred ninety-four crowns (86%) appeared natural in size, while 32 (14%) appeared bulky. A total of 199 crowns (88%) resisted fracture for at least 6 months, but 27 There was a significant increase in the incidence of attrition with the amount of time since crowns were placed (P=.007). There was also a significantly higher incidence of attrition in the crowns that were identified as being bulky (P=.045). Additionally, there was a significant increase in the incidence of trauma in patients with PVSSC fractures when compared to patients without attrition or fractures (P=.025).

There were no statistically significant differences in the prevalence of bruxism:

Historical or clinical	Tooth type receiving crown (tooth name)							
variable	E,F	D,G	C,H	O,P	N,Q	M,R	Row total	
Number placed	66	66	44	18	22	10	226	
Bruxing	6	4	12	4	4	2	32	
Fractured facing	5	9	10	1	0	2	27	
Wear	9	14	27	1	6	8	65	
Crazing	0	0	2	0	0	0	2	
Color change	0	0	1	0	0	2	3	
Crown size (bulky crowns)	6	4	12	4	4	2	32	

Table. DISTRIBUTION OF CROWN FINDING VARIABLES BY TOOTH TYPE.

- and trauma between patients with and without PVSSC attrition or fracture; and
- 2. between patients without PVSSC attrition or fracture and patients with fractures. Additionally, there were no gender differences in the number of fractured facings and presence of attrition and no significant increase in the number of fractures associated with the amount of time that had passed since crowns were placed.

Discussion

The vast majority (91%) of NuSmile crowns was placed under general anesthesia, and 96% of patients had positive behavior. Since preveneered crowns are less susceptible to local factors such as gingival hemorrhage, the authors conclude that the majority of the crowns evaluated in this study were placed under ideal conditions.

A total of 224 NuSmile crowns (99%) were retained at the time of examination. Despite some findings of clinical failure such as fractures and attrition, 91% of all patients maintained a good to excellent overall appearance after at least 6 months. NuSmile crowns are a clinically successful complete coverage restoration for anterior primary teeth, as evidenced by: (a) 86% resistance to fracture; (b) 71% resistance to attrition; (c) 99% retention; (d) 99% resistance to crazing; and (e) 99% color stability over a minimum of 6 months.

Despite the inability to crimp the crown's facial aspect, NuSmile crowns may be successfully retained after at least 6 months. Only 2 crowns (1%) had fallen off in 2 patients. Of these 2 patients, 1 crown was lost subsequent to trauma sustained from a fall. There was no statistically significant difference between: (1) first-year residents; (2) second-year residents; and (3) private practice practitioners in any variable. Dentists with all levels of experience had similar successful results in: (1) overall appearance; (2) resistance to wear; and (3) resistance to attrition.

Although canines were often the least observed, they represented the greatest number of failures. Canine NuSmile crowns were the only type to have color change or crazing and: (1) had the greatest number of fractures (44%); (2) had the

most noticeable wear (54%); and (3) were most likely to appear bulky (38%). The disproportionately higher number of failures in canine NuSmile crowns may be attributed to canine protected occlusion and, as the most likely crown type to be bulky, showed a statistically significant increase in the incidence of attrition.

All 226 crowns observed in this study were extra light, the original shade offered by NuSmile. This extra light shade was found to match only 2 of the patients' natural teeth (5%) and was lighter than the remaining unrestored teeth in 95% of patients. This color discrepancy was particularly noticeable when only a few teeth were restored with NuSmile crowns. To remedy this unnatural, "too white" appearance, NuSmile now offers a new light shade, slightly more yellow like natural teeth. Only 3 canine crowns (1%) were found to have a yellow color change when compared to a new, unused crown. The cause of this color change is unknown, but color changes in the crown facing have been observed following repeated steam sterilization. To decrease the risk of color change from repeat sterilization, careful crown selection prior to reducing the tooth may be the best approach.

The crown's length (regular or short) was not consistently recorded by the operator at the time of placement, and it was not always possible to determine the length of every NuSmile crown . As a result, no comparisons were made of: (1) either of the two commercially available crown lengths to margin; (2) position; (3) margin discolorization; or (4) gingival health. Examiners were not able to make adequate periapical films for all 46 study participants. Reasons for this failure include: (1) lack of patient maturity and cooperation; and (2) poor film placement. As a result, radiographic pulpal health and pulpal treatment were not included in the data analysis.

Bias may have been introduced, since the examiner may have placed some of the crowns in some subjects—although in the teaching setting, patients were often seen by multiple operators. In addition, because of this study's retrospective nature, the preoperative condition of the restored teeth was not known and variations in the size and shape of the prepared crown may have influenced results in some way. Finally, intra-and inter-rater reliability was not assessed and, in spite of calibration, variability may have existed since 3 examiners were involved.

Conclusion

Based on this study's results, the following conclusions can be made:

- 1. NuSmile crowns are a clinically successful restoration for anterior primary teeth.
- Despite some negative clinical changes, 91% of NuSmile crowns retain a good to excellent overall appearance after 6 months.
- Canine NuSmile crowns are the least clinically successful. They are most likely to fracture, wear, and appear bulky.
- 4. There is an increased incidence of attrition with increased time and with bulky crowns.
- 5. Successful results with NuSmile crowns may be obtained by both the experienced operator and the novice.

References

- Croll TP. Primary incisor restoration using resin-veneered stainless steel crowns. J Dent Child 1998;65:89-95.
- 2. Croll T, Helpin M. Preformed resin-veneered stainless steel crowns for restoration of primary incisors. Quintessence Int 1996;27:309-13.
- Tate AR, Ng MW, Needleman HL, Acs G. Failure rates of restorative procedures following dental rehabilitation under general anesthesia. Pediatr Dent 2002;24:69-71.
- 4. Brossok GE, Cullen CL. Nursing caries syndrome: Restorative options for primary anterior teeth. Compend Cont Educ Dent 1996;9:495-504.
- 5. Kopel HM, Beaver HA. Comprehensive restorative procedures for primary anteriors. J Dent Child 1967;34:412-23.
- 6. Lee JK. Restoration of primary anterior teeth: Review of the literature. Pediatr Dent 2002;24:506-10.
- Waggoner WF. Restoring primary anterior teeth. Pediatr Dent 2002;24:511-6.
- Waggoner WF, Cohen H. Failure strength of four veneered primary stainless steel crowns. Pediatr Dent 1995;17:36-40.
- Baker LH, Moon P, Mourino AP. Retention of esthetic veneers on primary stainless steel crowns. J Dent Child 1996;63:185-9.
- Roberts C, Lee JY, Wright JT. Clinical evaluation of and parental satisfaction with resin-faced stainless steel crowns. Pediatr Dent 2001;23:28-31.
- Kupietzky A, Waggoner WF, Galea J. The clinical and radiographic success of bonded resin composite strip crowns for primary incisors. Pediatr Dent 2003;25:577-81.
- Shah PV, Lee JY, Wright JT. Clinical success and parental satisfaction with anterior preveneered primary stainless steel crowns. Pediatr Dent 2004;26:391-5.

Abstract of Science of Literature

Two different protocols for hydroxyzine sedation

Dosages and schedules for oral administration of hydroxyzine have varied widely in clinical reports, ranging from 20 to 60 mg taken 45 minutes to 1 hour before treatment. The purpose of this study was to evaluate the effectiveness of sedation using two different dosages of hydroxyzine with nitrous oxide inhalation sedation. Thirty uncooperative, fearful children between 31 and 120 months old and ASA I were assigned randomly to 1 of 2 oral sedation treatment groups. Group 1 received 20 mg/kg hydroxyzine (Atarax) from the parents 24 hours prior to the procedure and 3.7 mg/kg hydroxyzine on the day of the procedure. Group 2 received 3.7 mg/kg hydroxyzine on the day of the procedure only. All patients in both groups received 50% nitrous oxide inhalation. The mean age of the children was 61.9 months (SD 11.9) for group 1 and 53.7 (SD 12.8) months for group 2. The overall sedation success rate was 90% regardless of group. There were no statistically significant differences between Groups 1 and 2. All the SaO2 readings were above 94%, which was not clinically significant. The authors concluded that there was no significant benefit of 20 mg hydroxyzine administered 24 hours preoperatively for the effective sedation of fearful and uncooperative children.

Comments: As with any other sedative agent, hydroxyzine should only be given by the dental provider, particularly when the results show that drugs given at home have no better effect on the behavior during sedation. *FMS*

Address correspondence to Zeynep Okte, Ankara Universitesi Dis Hekimligi Fakültesi, Pedodonti Anabilim Dali, 06500 Besevler/Ankara, Turkey; e-mail: zokte62@yahoo.com.

Faytrouny M, Okte Z, Kucukyavuz Z. Comparison of two different dosages of hydroxyzine for sedation in the paediatric dental patient. Int J Paediatr Dent 2007;17:378-82.

19 references

Abstracts of the Scientific Literature

Effect of age and sedative agent on the accuracy of bispectral index

The aim of this study was evaluate whether bispectral index (BIS) values could be correlated with 1) sedative agent used and 2) age of child. The BIS is a dimensionless number provided through neurophysiologic monitoring to theoretically indicate "depth of sedation/anesthesia.". This secondary analysis was performed from raw data of 4 independently conducted studies. Depth of sedation was noted using the 5-point University of Michigan Sedation Scale. Data for the BIS-sedative agent analysis was derived from 411 observations in 42 children. Data for the BIS-age of child analysis was derived from 983 observations in 128 children. BIS values were significantly lower in children <6 months age at each observed sedation level. BIS values decreased across sedation levels during the use of chloral hydrate, midazolam, propofol and pentobarbital. This decrease was not statistically significant. **Comments**: The use of BIS as a monitoring mechanism for children undergoing sedation is controversial. This study does emphasize that the use of BIS on children <6months of age or on children given opioids has limited clinical applications. While this study did not mention the clinical work performed under sedation or dosages of medications given, it does reflect the physiologic depth of sedation in children given midazolam and chloral hydrate, common medications used for oral sedation in dentistry. **ST** Address correspondence to Shobha Malviya, MD 1500 E.Medical Center Dr. Ann Arbor, MI 48109-0211; e-mail: smalviya@umich,edu. **Malviya S, Voepel-Lewis T, Tait A, Watcha M, Sadhasivam S, Friesen R. Effect of age and sedative agent on the accuracy of bispectral index in detecting depth of sedation in children. Pediatrics 2007;120:e461-e470.**

53 references

Does school or non-school environment contribute more to gains in childhood BMI?

The objective of this study was to see whether the school or non-school environments played a greater role in gains in body mass index (BMI) among young school aged children. Gains in BMI were calculated for children during the school year and over the summer vacation. In reality, this was a natural experiment in which, BMI measurements were obtained from 5,380 children attending 310 different schools. Data were from a subsample of children participating in the Early Childhood Longitudinal Study, Kindergarten Cohort. (ECLS-K). Statistical modeling was used to estimate gain rates in BMI. On average, BMI was measured in mid-October, and in early May. BMI gains over the school year were calculated by subtracting measures at the beginning of the school year with those from the end of the same academic year. Similarly, increases over the summer were calculated by subtracting values at the end of the previous school year from those at the beginning of the new academic year. Findings from this study reveal that growth in BMI was more than twice as fast during summer vacation than during the school year. All children, including those who were overweight, underweight, and of average weight showed healthier growth patterns during the school year than during summer break. Overall, the environment outside of school may contribute more to young children being overweight than the school setting. **Comments:** Theses findings are interesting but the authors do not speculate as to why this pattern was observed. It might be that children get more physical activity over the course of the school year and may snack less while they are at school than over the summer break. Nonetheless, parents need to keep children on a regimen conducive to health even while on vacation, which would include both exercise and limits on snacks and over eating. Abalanced approach is needed to support activity both in the classroom and at home. **RJS**

Address correspondence to Dr. Paul T. von Hippel, Department of Sociology, Ohio State University, 300 Bricker Hall, 190 N Oval Mall, Columbus, OH 43210; e-mail: von-hippel.1@sociology.osu.edu.

von Hippel PT, Powell B, Downey DB, Rowland NJ. The effect of school on overweight in childhood: gain in body mass index during the school year and during summer vacation. Am J Public Health. 2007;97:696-702.

35 references

Copyright of Pediatric Dentistry is the property of American Society of Dentistry for Children and its content may not be copied or emailed to multiple sites or posted to a listserv without the copyright holder's express written permission. However, users may print, download, or email articles for individual use.